


OIL ANALYSIS REPORT

sa Sa



NORMAL



Machine Id **8117064**

Component **Diesel Engine**

Fluid

DIESEL ENGINE OIL SAE 10W30 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | Jan 2021 | Sep2021 | Mar2023 Jun2023 | Oct2023 | |
|------------------|----------|-------------|------------|-----------------|-------------|-------------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | IL06009297 | IL05911754 | IL05828773 |
| Sample Date | | Client Info | | 24 Oct 2023 | 16 Jun 2023 | 31 Mar 2023 |
| Machine Age | mls | Client Info | | 182350 | 163896 | 150796 |
| Oil Age | mls | Client Info | | 40000 | 40000 | 40000 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATION | 1 | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 12 | 41 | 23 |
| Chromium | ppm | ASTM D5185m | >20 | 1 | 1 | 2 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 7 | 18 | 9 |
| Lead | ppm | ASTM D5185m | >40 | 3 | 0 | <1 |
| Copper | ppm | ASTM D5185m | >330 | 1 | 2 | 1 |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | <1 |
| Antimony | ppm | ASTM D5185m | | | | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 250 | 19 | 23 | 20 |
| Barium | ppm | ASTM D5185m | 10 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 100 | 41 | 50 | 46 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | 1 |
| Magnesium | ppm | ASTM D5185m | 450 | 487 | 511 | 492 |
| Calcium | ppm | ASTM D5185m | 3000 | 1602 | 1766 | 1491 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 718 | 717 | 679 |
| Zinc | ppm | ASTM D5185m | 1350 | 891 | 951 | 879 |
| Sulfur | ppm | ASTM D5185m | 4250 | 2323 | 2412 | 2260 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 6 | 7 | 8 |
| Sodium | ppm | ASTM D5185m | | 3 | 6 | 2 |
| Potassium | ppm | ASTM D5185m | >20 | 14 | 15 | 19 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.4 | 0.6 | 0.4 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 10.9 | 14.9 | 10.8 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 23.1 | 25.2 | 21.2 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 24.0 | 27.1 | 22.7 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 7.0 | 7.6 | 6.3 |




OIL ANALYSIS REPORT








| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |

| FLUID PROPER | TIES | method | | | | history2 |
|--------------|------|-----------|------|------|------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 10.9 | 11.2 | 11.5 | 11.0 |













Laboratory Sample No. Lab Number Unique Number : 10743059 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : IL06009297 : 06009297

Received Diagnosed : 16 Nov 2023 : 16 Nov 2023

Diagnostician : Wes Davis

IDEALEASE OF ATLANTA - FULTON

4675 BAKERS FERRY ROAD ATLANTA, GA US 30331

Contact: DAVID JOHNS davidjohns@idealease.com

T: (404)699-5571 F: (404)699-7420

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: IDEATLGA [WUSCAR] 06009297 (Generated: 11/16/2023 18:57:11) Rev: 1

Contact/Location: DAVID JOHNS - IDEATLGA