




# PROBLEM SUMMARY

## Sample Rating Trend

ISO




Area  
**412**  
 Machine Id  
**273 BANBURY MOTOR**  
 Component  
**Inboard Journal Bearing**  
 Fluid  
**ESSO NUTO H ISO 68 (1 QTS)**



## COMPONENT CONDITION SUMMARY

### ▲ Particle Trend



## RECOMMENDATION

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status			<b>ABNORMAL</b>	ABNORMAL	ABNORMAL
Particles >4µm	ASTM D7647	>10000	▲ <b>38069</b>	▲ 29841	▲ 83339
Particles >6µm	ASTM D7647	>2500	▲ <b>4127</b>	▲ 3129	▲ 12209
Oil Cleanliness	ISO 4406 (c)	>20/18/14	▲ <b>22/19/13</b>	▲ 22/19/14	▲ 24/21/16

Customer Id: BRIDES  
 Sample No.: WC0838935  
 Lab Number: 06009522  
 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Don Baldrige +1  
[don.b505@comcast.net](mailto:don.b505@comcast.net)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

*There are no recommended actions for this sample.*

## HISTORICAL DIAGNOSIS

### 05 Jul 2023 Diag: Angela Borella

ISO



No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 09 Apr 2023 Diag: Jonathan Hester

ISO



The oil change at the time of sampling has been noted. We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 25 Nov 2022 Diag: Don Baldrige

ISO



No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


view report





# OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Area  
**412**  
 Machine Id  
**273 BANBURY MOTOR**  
 Component  
**Inboard Journal Bearing**  
 Fluid  
**ESSO NUTO H ISO 68 (1 QTS)**

## DIAGNOSIS

### Recommendation

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0838935</b>	WC0640598	WC0569570
Sample Date	Client Info		<b>10 Nov 2023</b>	05 Jul 2023	09 Apr 2023
Machine Age	mths	Client Info	<b>6</b>	6	0
Oil Age	mths	Client Info	<b>0</b>	0	4
Oil Changed	Client Info		<b>Changed</b>	Changed	Changed
Sample Status			<b>ABNORMAL</b>	ABNORMAL	ABNORMAL

## WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184		<b>11</b>	14	8
Iron	ppm	ASTM D5185m >60	<b>0</b>	<1	0
Chromium	ppm	ASTM D5185m >20	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m >20	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m	<b>0</b>	0	0
Silver	ppm	ASTM D5185m	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >4	<b>&lt;1</b>	<1	0
Lead	ppm	ASTM D5185m >250	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m >125	<b>&lt;1</b>	5	<1
Tin	ppm	ASTM D5185m >80	<b>4</b>	4	4
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	<b>0</b>	0	0
Barium	ppm	ASTM D5185m 0	<b>7</b>	0	0
Molybdenum	ppm	ASTM D5185m 0	<b>0</b>	<1	<1
Manganese	ppm	ASTM D5185m	<b>0</b>	0	<1
Magnesium	ppm	ASTM D5185m 5	<b>&lt;1</b>	0	4
Calcium	ppm	ASTM D5185m 50	<b>48</b>	39	49
Phosphorus	ppm	ASTM D5185m 330	<b>321</b>	332	335
Zinc	ppm	ASTM D5185m 420	<b>402</b>	416	433
Sulfur	ppm	ASTM D5185m 3100	<b>3246</b>	3087	2657

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >50	<b>4</b>	12	35
Sodium	ppm	ASTM D5185m	<b>0</b>	0	0
Potassium	ppm	ASTM D5185m >20	<b>&lt;1</b>	1	0






## FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>10000	<b>▲ 38069</b>	▲ 29841	▲ 83339
Particles >6µm	ASTM D7647	>2500	<b>▲ 4127</b>	▲ 3129	▲ 12209
Particles >14µm	ASTM D7647	>160	<b>80</b>	116	▲ 457
Particles >21µm	ASTM D7647	>40	<b>15</b>	27	▲ 104
Particles >38µm	ASTM D7647	>10	<b>1</b>	2	7
Particles >71µm	ASTM D7647	>3	<b>0</b>	0	0
Oil Cleanliness	ISO 4406 (c)	>20/18/14	<b>▲ 22/19/13</b>	▲ 22/19/14	▲ 24/21/16

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 .40	<b>0.37</b>	0.39	0.38

# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	68.8	68.3	69.1

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0838935 **Received** : 16 Nov 2023  
**Lab Number** : 06009522 **Diagnosed** : 19 Nov 2023  
**Unique Number** : 10743284 **Diagnostician** : Don Baldrige  
**Test Package** : IND 2 ( Additional Tests: PQ, PrtCount )

**BRIDGESTONE FIRESTONE - DES MOINES**  
 4600 NW 2ND AVE  
 DES MOINES, IA  
 US 50313  
 Contact: SCOTT CARTER  
 CarterScottA@FirestoneAg.com  
 T: x:  
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)