


PROBLEM SUMMARY

Area 412 Machine Id CARBON BLACK PURGE BLOWER

Inboard Bearing Fluid ESSO NUTO H ISO 68 (1 QTS)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Sample Rating Trend

PROBLEMATIC TEST RESULTS						
Sample Status			ABNORMAL	ABNORMAL	ABNORMAL	
Particles >4µm	ASTM D7647	>10000	🔺 24656	<u> </u>	▲ 96336	
Particles >6µm	ASTM D7647	>2500	6215	🔺 22519	🔺 25666	
Particles >14µm	ASTM D7647	>160	<u> </u>	<u> </u>	<u> </u>	
Particles >21µm	ASTM D7647	>40	4 9	20	<u> </u>	
Oil Cleanliness	ISO 4406 (c)	>20/18/14	<u> </u>	<u> </u>	4 /22/16	

Customer Id: BRIDES Sample No.: WC0838844 Lab Number: 06009537 Test Package: IND 2



To manage this report scan the QR code


To discuss the diagnosis or test data: Don Baldridge +1 <u>don.b505@comcast.net</u>

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS

There are no recommended actions for this sample.

HISTORICAL DIAGNOSIS



The oil change at the time of sampling has been noted. We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

30 Dec 2022 Diag: Angela Borella

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

06 Jul 2022 Diag: Doug Bogart



The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



view report





OIL ANALYSIS REPORT

Area 412 Machine Id CARBON BLACK PURGE BLOWER

Inboard Bearing Fluid ESSO NUTO H ISO 68 (1 QTS)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0838844	WC0569566	WC0640535
Sample Date		Client Info		10 Nov 2023	09 Apr 2023	30 Dec 2022
Machine Age	mths	Client Info		6	0	6
Oil Age	mths	Client Info		0	4	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184		8	6	12
Iron	ppm	ASTM D5185m	>20	<1	<1	1
Chromium	ppm	ASTM D5185m	>20	0	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	0	0
Lead	ppm	ASTM D5185m		<1	0	0
Copper	ppm	ASTM D5185m	>20	3	<1	1
Tin	ppm	ASTM D5185m		<1	0	0
Vanadium	ppm	ASTM D5185m	220	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	ppin		11			
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m		7	0	1
Molybdenum	ppm	ASTM D5185m	0	0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	5	<1	5	2
Calcium	ppm	ASTM D5185m	50	41	50	53
Phosphorus	ppm	ASTM D5185m	330	323	344	334
Zinc	ppm	ASTM D5185m	420	383	442	441
Sulfur	ppm	ASTM D5185m	3100	2809	2723	2395
CONTAMINANTS	S	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2	2	2
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	4 24656	102671	▲ 96336
Particles >6µm		ASTM D7647	>2500	<u> </u>	<u> </u>	▲ 25666
Particles >14µm		ASTM D7647	>160	A 213	2 02	▲ 569
Particles >21µm		ASTM D7647	>40	<u> </u>	20	A 80
Particles >38µm		ASTM D7647	>10	2	0	5
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/14	A 22/20/15	▲ 24/22/15	▲ 24/22/16
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	.40	0.38	0.41	0.42
· /	5 5					



Acid Number

0.50

(B/HOX

Acid Number (mg)

0.00

80

7

0,70 0

-*3 6!

60

55

250

200


150

100

50


0

OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	68.8	65.8	65.4	63.3
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color				•		

Bottom



Contact/Location: SCOTT CARTER - BRIDES