


# **OIL ANALYSIS REPORT**

### **Sample Rating Trend**







## Machine Id A502 Component

**Hydraulic System** 

**MOBIL DTE 10 EXCEL 32 (43 GAL)** 

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.


### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM   | MATION | method       | limit/base | current     | history1    | history2    |
|-----------------|--------|--------------|------------|-------------|-------------|-------------|
| Sample Number   |        | Client Info  |            | MHI026281   | MHI025117   | MHI017014   |
| Sample Date     |        | Client Info  |            | 02 Nov 2023 | 04 Oct 2022 | 06 Oct 2021 |
| Machine Age     | hrs    | Client Info  |            | 0           | 0           | 0           |
| Oil Age         | hrs    | Client Info  |            | 92363       | 85795       | 79921       |
| Oil Changed     |        | Client Info  |            | Not Changd  | Not Changd  | Not Changd  |
| Sample Status   |        |              |            | NORMAL      | NORMAL      | NORMAL      |
| WEAR METALS     |        | method       | limit/base | current     | history1    | history2    |
| Iron            | ppm    | ASTM D5185m  | >50        | 16          | 12          | 8           |
| Chromium        | ppm    | ASTM D5185m  | >20        | 0           | <1          | <1          |
| Nickel          | ppm    | ASTM D5185m  | >20        | 12          | 10          | 4           |
| Titanium        | ppm    | ASTM D5185m  |            | 0           | 0           | 0           |
| Silver          | ppm    | ASTM D5185m  |            | 0           | 0           | 0           |
| Aluminum        | ppm    | ASTM D5185m  | >20        | <1          | <1          | 0           |
| Lead            | ppm    | ASTM D5185m  | >20        | 1           | <1          | <1          |
| Copper          | ppm    | ASTM D5185m  | >20        | <1          | <1          | <1          |
| Tin             | ppm    | ASTM D5185m  | >20        | 0           | 0           | <1          |
| Antimony        | ppm    | ASTM D5185m  |            |             |             | 0           |
| Vanadium        | ppm    | ASTM D5185m  |            | 0           | 0           | 0           |
| Cadmium         | ppm    | ASTM D5185m  |            | 0           | 0           | 0           |
| ADDITIVES       |        | method       | limit/base | current     | history1    | history2    |
| Boron           | ppm    | ASTM D5185m  |            | 0           | <1          | 2           |
| Barium          | ppm    | ASTM D5185m  |            | 6           | 0           | 0           |
| Molybdenum      | ppm    | ASTM D5185m  |            | 0           | 0           | 0           |
| Manganese       | ppm    | ASTM D5185m  |            | 0           | <1          | 0           |
| Magnesium       | ppm    | ASTM D5185m  |            | <1          | 0           | <1          |
| Calcium         | ppm    | ASTM D5185m  | 120        | 130         | 112         | 119         |
| Phosphorus      | ppm    | ASTM D5185m  | 475        | 520         | 445         | 454         |
| Zinc            | ppm    | ASTM D5185m  |            | 29          | 1           | 25          |
| Sulfur          | ppm    | ASTM D5185m  | 1275       | 2414        | 1981        | 1790        |
| CONTAMINANTS    | ;      | method       | limit/base | current     | history1    | history2    |
| Silicon         | ppm    | ASTM D5185m  | >+30       | 0           | <1          | <1          |
| Sodium          | ppm    | ASTM D5185m  |            | 0           | 2           | 2           |
| Potassium       | ppm    | ASTM D5185m  |            | <1          | 0           | 0           |
| Water           | %      | ASTM D6304   | >0.1       | 0.006       | 0.008       | 0.003       |
| ppm Water       | ppm    | ASTM D6304   | >1000      | 64.6        | 82.5        | 37.3        |
| FLUID CLEANLIN  | IESS   | method       | limit/base | current     | history1    | history2    |
| Particles >4µm  |        | ASTM D7647   | >5000      | 941         | 1732        | 1033        |
| Particles >6µm  |        | ASTM D7647   | >1300      | 223         | 326         | 398         |
| Particles >14µm |        | ASTM D7647   | >160       | 23          | 24          | 49          |
| Particles >21µm |        | ASTM D7647   | >40        | 9           | 8           | 13          |
| Particles >38µm |        | ASTM D7647   | >10        | 0           | 0           | 0           |
| Particles >71μm |        | ASTM D7647   | >3         | 0           | 0           | 0           |
| Oil Cleanliness |        | ISO 4406 (c) | >19/17/14  | 17/15/12    | 18/16/12    | 17/16/13    |
| FLUID DEGRADA   | MOITA  | method       | limit/base | current     | history1    | history2    |



## **OIL ANALYSIS REPORT**



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (760)329-7122