

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Component Compressor

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

KAESER 7083990

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA009769	KCP53925	KCP47692D
Sample Date		Client Info		02 Nov 2023	02 May 2023	22 Nov 2022
Machine Age	hrs	Client Info		27460	24295	21051
Oil Age	hrs	Client Info		0	3243	3528
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	0	1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	<1	0	0
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm		>50	4	3	2
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m	210	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	6	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	90	6	28	45
Calcium	ppm	ASTM D5185m	2	<1	0	0
Phosphorus	ppm	ASTM D5185m		17	0	25
Zinc	ppm	ASTM D5185m		<1	12	6
Sulfur	ppm	ASTM D5185m		19242	19188	20210
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	5	2	2
Sodium	ppm	ASTM D5185m		5	14	23
Potassium	ppm	ASTM D5185m	>20	3	4	5
Water	%	ASTM D6304	>0.05	0.012	0.014	0.019
ppm Water	ppm	ASTM D6304	>500	122.9	148.4	196.5
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		2736	3300	7102
Particles >6µm		ASTM D7647	>1300	796	930	1 893
Particles >14µm		ASTM D7647	>80	63	68	🔺 145
Particles >21µm		ASTM D7647	>20	15	16	A 39
Particles >38µm		ASTM D7647	>4	1	1	2
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	19/17/13	19/17/13	▲ 20/18/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.33	0.34	0.37


Contact/Location: Service Manager - AMACOPTX



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.1	43.9	43.8
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				a		
				11 - Carlos		

Bottom

