




OIL ANALYSIS REPORT



Area
605 Ultra 40 TRIAL
 Machine Id
Pinconning CAT 2 PINM02BE
 Component
Biogas Engine
 Fluid
CHEVRON HDAX 6500 LFG GAS ENGINE OIL (--- GAL)

Sample Rating Trend



NORMAL



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0840777	WC0840776	WC0531420
Sample Date	Client Info		13 Nov 2023	03 Nov 2023	31 May 2023
Machine Age	hrs	Client Info	44917	58965	58965
Oil Age	hrs	Client Info	156	44636	876
Oil Changed	Client Info		Changed	Changed	Not Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<1.0	<1.0	<1.0
Water	WC Method	>0.1	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >15	1	<1	1
Chromium	ppm	ASTM D5185m >4	0	0	0
Nickel	ppm	ASTM D5185m >2	0	0	0
Titanium	ppm	ASTM D5185m	0	0	<1
Silver	ppm	ASTM D5185m >5	0	0	0
Aluminum	ppm	ASTM D5185m >6	<1	<1	<1
Lead	ppm	ASTM D5185m >9	0	0	0
Copper	ppm	ASTM D5185m >6	3	3	<1
Tin	ppm	ASTM D5185m >4	<1	<1	1
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	7	15	5
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	2	<1	2
Manganese	ppm	ASTM D5185m	<1	0	<1
Magnesium	ppm	ASTM D5185m	19	5	15
Calcium	ppm	ASTM D5185m	1591	1523	1788
Phosphorus	ppm	ASTM D5185m	245	245	299
Zinc	ppm	ASTM D5185m	343	319	358
Sulfur	ppm	ASTM D5185m	2357	2115	3307

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >181	60	29	125
Sodium	ppm	ASTM D5185m	4	5	1
Potassium	ppm	ASTM D5185m >20	<1	2	0

INFRA-RED




	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	0	0.1
Nitration	Abs/cm	*ASTM D7624 >20	4.1	4.0	6.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	15.7	15.5	21.4

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	8.0	8.3	15.9
Acid Number (AN)	mg KOH/g	ASTM D8045 1.2	0.45	0.60	1.33
Base Number (BN)	mg KOH/g	ASTM D2896 4.5	4.05	5.34	4.00











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	14.7	13.7	13.6	14.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0840777 **Recieved** : 16 Nov 2023
Lab Number : 06009771 **Diagnosed** : 17 Nov 2023
Unique Number : 10748915 **Diagnostician** : Doug Bogart
Test Package : MOB 2

EDL NA Recips-Pinconning
 Pinconning Powerstation, 2403 E. Whitefeather Road
 Pinconning, MI
 US 48650
 Contact: DOUG HINE
 doug.hine@edlenergy.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)