


OIL ANALYSIS REPORT

⊤ Sai



NORMAL



Machine Id 1712 Component Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		Sej	2023	0ct2023 0ct2	123	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0855851	WC0855865	WC0855909
Sample Date		Client Info		31 Oct 2023	05 Oct 2023	13 Sep 2023
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	9	8	<1
Chromium	ppm	ASTM D5185m	>20	<1	<1	0
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	1
Lead	ppm	ASTM D5185m		0	0	0
Copper	ppm	ASTM D5185m		<1	1	2
Tin	ppm	ASTM D5185m		<1	<1	0
Vanadium	ppm	ASTM D5185m	7.0	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	2	2	<1
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	58	60	58
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m	450	949	945	962
Calcium	ppm	ASTM D5185m	3000	1068	1137	1110
Phosphorus	ppm	ASTM D5185m	1150	1039	1058	1075
Zinc	ppm	ASTM D5185m	1350	1292	1324	1324
Sulfur	ppm	ASTM D5185m	4250	3015	3168	3334
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	5	3
Sodium	ppm	ASTM D5185m		<1	2	3
Potassium	ppm	ASTM D5185m	>20	0	1	1
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.5	0.3	0.1
Nitration	Abs/cm	*ASTM D7624	>20	7.6	7.1	5.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	20.2	18.1
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.2	17.5	14.7
Base Number (BN)	mg KOH/g	ASTM D2896		8.1	7.2	9.0
= 300 : 10:11001 (D14)	9		5.0			0.0




OIL ANALYSIS REPORT

cSt

ASTM D445 14.4

Visc @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES r		method	limit/base	current	history1	history2

14.0

14.0

14.3

V100 @ 100 O	710	IIII D 1 1 1 . 1	14.0	14.0	14.0
GRAPHS					
Iron (ppm)			Lead (ppm)		
Severe	1	-	Severe		
			00		
Abnormal		-	Abnormal		
50			20		
3/23	Oct5/23 -	0ct31/23	3/23	Oct5/23	5
Sep 13/23	0	0ct3	Sep 13/23	Oct	ć
Aluminum (ppm	1)		Chromium (ppm)	
Severe			Severe		
Abnormal			€ 30		
20 - Abnormal			Abnormal		
0			10		
Sep13/23	Oct5/23 -	0ct31/23	Sep13/23	Oct5/23 -	6
	0	Oct3			
Copper (ppm)			Silicon (ppm)	
Severe 2001			60		
00			E 40		
00			Abnormal		
0			0		
Sep13/23-	Oct5/23 -	Oct31/23	Sep 13/23	Oct5/23 -	
		Oct			
Viscosity @ 100	°C		Base Numbe	er	
Abnormal			Abnormal Abnormal		
Base Abnormal			Abnomal Abnomal Abnomal		
Abnormal		1	5.0 Abnormal		





Laboratory Sample No. Lab Number Unique Number : 10749775

: WC0855851 : 06010631

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 19 Nov 2023 Diagnostician : Wes Davis

: 17 Nov 2023

Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GO DURHAM - RAPT 1903 FAYETTEVILLE ST DURHAM, NC

US 27701 Contact: Robert Iosiniecki

Robert.losiniecki@ratpdev.com

T:

F: