

OIL ANALYSIS REPORT

Sample Rating Trend



Area JBS 310 PLUS Machine Id 93422 - PERMA PIPE Component

Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

			May2023	Nov2023		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06010994	UCH05843437	
Sample Date		Client Info		07 Nov 2023	03 May 2023	
Machine Age	hrs	Client Info		46472	46437	
Oil Age	hrs	Client Info		35	126	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS			limit/base	current		history ()
		method			history1	history2
Iron	ppm	ASTM D5185m	>50	<1	4	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	0	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	0	<1	
Tin	ppm	ASTM D5185m	>15	<1	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0.3	0	0	
Barium	ppm	ASTM D5185m	0.3	0	2	
Molybdenum	ppm	ASTM D5185m	0	0	0	
Manganese	ppm	ASTM D5185m	0.9	0	0	
Magnesium	ppm	ASTM D5185m	0.2	0	<1	
Calcium	ppm	ASTM D5185m	0.1	0	0	
Phosphorus	ppm	ASTM D5185m	429	458	425	
Zinc	ppm	ASTM D5185m	0.3	9	23	
Sulfur	ppm	ASTM D5185m	1336	989	433	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	
Sodium	ppm	ASTM D5185m		0	0	
Potassium	ppm	ASTM D5185m	>20	0	<1	
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.622	0.70	0.80	




35 May3/23

ĕ

OIL ANALYSIS REPORT

VISUAL



	VISUAL		methou			history i	TIIStOLYZ
	White Metal	scalar *	*Visual	NONE	NONE	NONE	
	Yellow Metal			NONE	NONE	NONE	
	Precipitate			NONE	NONE	NONE	
	Silt			NONE	NONE	NONE	
	Debris			NONE	NONE	NONE	
	Sand/Dirt			NONE	NONE	NONE	
23	Appearance			NORML	NORML	NORML	
Nav7/23							
	Odor			NORML	NORML	NORML	
	Emulsified Water			>0.1	NEG	NEG	
	Free Water	scalar *	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt A	ASTM D445	44.32	48.1	49.0	
	SAMPLE IMAGES	S	method	limit/base	current	history1	history2
Nov7/23	Color						no image
	Bottom						no image
	Non-ferrous Metal	S		Nov7/23 8			
	Viscosity @ 40°C			(0)1.00 (0)400 0.80 bill 0.60 bill 0.60 bill 0.60 bill 0.40 bill 0.20 bill 0	Acid Number Base		
Laboratory Sample No. Lab Number Unique Number Test Package iscuss this sample report,	: WearCheck USA - 5 : UCH06010994 : 06010994 : 10750138 : IND 2	Received Diagnosed Diagnostic	: 17 N d : 21 N cian : Don 0-237-1369	ry, NC 27513 lov 2023 lov 2023 Baldridge		NA Contact: HE herb.dewees@j	ARD & SON ARRISON ST ASHVILLE, TI US 3720 ERB DEWEE

ч

Contact/Location: HERB DEWEES - UCJOHNAS