

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area NOT GIVEN Machine Id DATTCO MIDDLE TOWN Component

Gearbox Fluid NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

		-		Nov2023		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06010999		
Sample Date		Client Info		18 Nov 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	۷	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	0		
Chromium	ppm	ASTM D5185m	>15	0		
Nickel	ppm	ASTM D5185m	>15	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>100	0		
Copper	ppm	ASTM D5185m	>200	<1		
Tin	ppm	ASTM D5185m	>25	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		638		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		615		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	2		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.08		



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	MODER		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
8/23 -	Appearance	scalar	*Visual	NORML	NORML		
Nov18/23	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Free Water	scalar	*Visual		NEG		
-	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		43.4		
	SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Nov18/23	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metal	5		Nov18/23			
	Viscosity @ 40°C			Nov18/23	Acid Number		
	200 Abnormal			0.10 0.10 0.00 0.00 400 400 400 400 400	Nov18/23		
Laboratory Sample No. Lab Number Unique Number	: WearCheck USA - 5 : UHK06010999 I : 06010999 I		CONNECTICUT COMPRESSOR SYSTEM PLAINVILLE, C US 0606 Contact: KEVI reports@ctcompressor.co				

ñ

Contact/Location: KEVIN ? - UCCONPLA

Page 2 of 2