

## **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL





Transmission Fluid

### CASTROL TRANSYND 668 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the fluid.

### Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0841473		
Sample Date		Client Info		31 Oct 2023		
Machine Age	hrs	Client Info		7655		
Oil Age	hrs	Client Info		3300		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>320	19		
Chromium	ppm	ASTM D5185m	>5	0		
Nickel	ppm	ASTM D5185m	>5	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>50	10		
Lead	ppm	ASTM D5185m	>65	1		
Copper	ppm	ASTM D5185m	>95	10		
Tin	ppm	ASTM D5185m	>6	2		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		77		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		2		
Calcium	ppm	ASTM D5185m		180		
Phosphorus	ppm	ASTM D5185m		255		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		1649		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>65	3		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	0		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		

Contact/Location: Service Manager - AVWSEW



# **OIL ANALYSIS REPORT**



	FLUID PROPERTIES		method limit/base		current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	33	32.7		
	SAMPLE IMAG	iES	method	limit/base	current	history1	history
	Color				no image	no image	no image
31/23							
20	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys						
	18 - iron chromium						
	16 minimum nickel						
F	12						
1100	<u>5</u> 10 8						
	6 -						
	4						
	)ct31/2			Jct31/2			
	 Non-ferrous Me	tals		0			
	10 copper j						
	8 - tin						
	7						
maa	Ed. 5 -						
	4						
	2						
	1						
	31/23			31/23			
	Viscosity @ 400	c		Oct			
	<sup>38</sup>						
	36 Abnormal						
	35						
40°C)	34 33 Base						
cSt	<sup>3</sup> 32						
	31						
	29 Abnormal						
	1 I I						
	28			23			

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: