

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **29 - HUSKY 2** Component Hydraulic System Fluid AW HYDRAULIC OIL ISO 46 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please note that this is a corrected copy for data entry updates.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.






SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PTK0004554	PTK0003880	PTK0002742
Sample Date		Client Info		18 Oct 2023	27 Mar 2023	23 May 2022
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Oil Changed	interio	Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	7	1
Chromium	ppm	ASTM D5185m		0	<1	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m	0	0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	0	0
Lead	ppm	ASTM D5185m	>20	0	0	0
Copper	ppm	ASTM D5185m		<1	<1	0
Tin	ppm	ASTM D5185m	>20	0	0	0
Vanadium	ppm	ASTM D5185m	20	<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	۰ <1	0	0
Manganese	ppm	ASTM D5185m	0	0	0	0
Magnesium	ppm	ASTM D5185m	25	0	0	0
Calcium	ppm	ASTM D5185m	200	0	0	0
Phosphorus	ppm	ASTM D5185m	300	51	118	151
Zinc	ppm	ASTM D5185m	370	9	44	52
Sulfur	ppm	ASTM D5185m	2500	0	68	108
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		8	6	2
Sodium	ppm	ASTM D5185m	210	1	0	<1
Potassium	ppm	ASTM D5185m	>20	0	<1	0
FLUID CLEANLIN		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	144	541	227
Particles >6µm		ASTM D7647		49	100	56
Particles >14µm		ASTM D7647 ASTM D7647	>160	6	18	7
Particles >21µm		ASTM D7647		1	6	2
Particles >38µm		ASTM D7647	>10	0	0	0
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	0 14/13/10	14/11	13/10
FLUID DEGRADA	TION _	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.34	0.41	0.40
	ing itoring	, 10 HM D0040	5.67	0.07	V-T I	0.40


Report Id: NIAPUY [WUSCAR] 06012351 (Generated: 12/02/2023 04:43:32) Rev: 2


Contact/Location: ANDREW Luebbehusen - NIAPUY




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.1	45.6	45.8
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color						
Bottom						



Ĕ

Contact/Location: ANDREW Luebbehusen - NIAPUY