




# PROBLEM SUMMARY


Sample Rating Trend



Machine Id  
**KAESER SFC30ST 4018723 (S/N 1050)**  
 Component  
**Compressor**  
 Fluid  
**KAESER SIGMA (OEM) S-460 (--- GAL)**

## COMPONENT CONDITION SUMMARY

▲ Particle Trend



## RECOMMENDATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status		ATTENTION	ABNORMAL	ATTENTION
Particles >6µm	ASTM D7647 >1300	▲ 1462	---	▲ 1964
Oil Cleanliness	ISO 4406 (c) >--/17/13	▲ 19/18/13	---	▲ 20/18/14

Customer Id: CCLSAI  
 Sample No.: KCPA009761  
 Lab Number: 06012392  
 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Don Baldrige +1  
[don.b505@comcast.net](mailto:don.b505@comcast.net)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

*There are no recommended actions for this sample.*

## HISTORICAL DIAGNOSIS

### 06 Mar 2023 Diag: Doug Bogart

#### VIS DEBRIS



No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample. All component wear rates are normal. Moderate concentration of visible dirt/debris present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 09 Aug 2022 Diag: Don Baldrige

#### ISO



No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a moderate amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 23 Nov 2021 Diag: Jonathan Hester

#### NORMAL




Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the component. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



# OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id  
**KAESER SFC30ST 4018723 (S/N 1050)**

Component

**Compressor**

Fluid

**KAESER SIGMA (OEM) S-460 (--- GAL)**

## DIAGNOSIS

### ▲ Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### ▲ Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>KCPA009761</b>	KCP54479	KCP49794
Sample Date	Client Info		<b>02 Nov 2023</b>	06 Mar 2023	09 Aug 2022
Machine Age	hrs	Client Info	<b>63692</b>	60065	57279
Oil Age	hrs	Client Info	<b>0</b>	2450	2900
Oil Changed	Client Info		<b>N/A</b>	Not Changd	Changed
Sample Status			<b>ATTENTION</b>	ABNORMAL	ATTENTION

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	<b>0</b>	0	0
Chromium	ppm	ASTM D5185m >10	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m >3	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m >3	<b>0</b>	0	0
Silver	ppm	ASTM D5185m >2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m >10	<b>0</b>	<1	<1
Lead	ppm	ASTM D5185m >10	<b>0</b>	0	0
Copper	ppm	ASTM D5185m >50	<b>12</b>	4	10
Tin	ppm	ASTM D5185m >10	<b>&lt;1</b>	0	<1
Vanadium	ppm	ASTM D5185m	<b>&lt;1</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	<b>0</b>	0	0
Barium	ppm	ASTM D5185m 90	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	<b>0</b>	0	0
Manganese	ppm	ASTM D5185m	<b>0</b>	<1	0
Magnesium	ppm	ASTM D5185m 90	<b>0</b>	47	6
Calcium	ppm	ASTM D5185m 2	<b>0</b>	0	0
Phosphorus	ppm	ASTM D5185m	<b>0</b>	33	2
Zinc	ppm	ASTM D5185m	<b>0</b>	9	15
Sulfur	ppm	ASTM D5185m	<b>14465</b>	21427	18172

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	<b>&lt;1</b>	3	0
Sodium	ppm	ASTM D5185m	<b>&lt;1</b>	10	3
Potassium	ppm	ASTM D5185m >20	<b>0</b>	<1	0
Water	%	ASTM D6304 >0.05	<b>0.008</b>	0.011	0.011
ppm Water	ppm	ASTM D6304 >500	<b>84.6</b>	112.2	110.2

## FLUID CLEANLINESS


	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		<b>4757</b>	---	6164
Particles >6µm	ASTM D7647	>1300	▲ <b>1462</b>	---	▲ 1964
Particles >14µm	ASTM D7647	>80	<b>52</b>	---	▲ 158
Particles >21µm	ASTM D7647	>20	<b>13</b>	---	▲ 26
Particles >38µm	ASTM D7647	>4	<b>0</b>	---	2
Particles >71µm	ASTM D7647	>3	<b>0</b>	---	1
Oil Cleanliness	ISO 4406 (c)	>--/17/13	▲ <b>19/18/13</b>	---	▲ 20/18/14

## FLUID DEGRADATION


	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 0.4	<b>0.32</b>	0.40	0.31

# OIL ANALYSIS REPORT


### ▲ Particle Trend




### Water (KF)




### Acid Number



### Water (KF)



### Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.1	44.4

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color




Bottom




### GRAPHS


#### Ferrous Alloys




#### Non-ferrous Metals




#### Viscosity @ 40°C



#### ▲ Particle Count



#### Acid Number



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : KCPA009761 **Received** : 20 Nov 2023  
**Lab Number** : 06012392 **Diagnosed** : 22 Nov 2023  
**Unique Number** : 10751536 **Diagnostician** : Don Baldrige

**CCL LABEL - ST LOUIS INC**  
 208 SPRING DR  
 SAINT CHARLES, MO  
 US 63303  
 Contact: B. MARTIN  
 bmartin@cclind.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: