

# **OIL ANALYSIS REPORT**

## NOT GIVEN **ÄTLAS COPCO API615-957 - FABRICAL 2** Component

Compressor

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.






SAMPLE INFORM	<b>NATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06012574		
Sample Date		Client Info		16 Oct 2023		
Machine Age	hrs	Client Info		42123		
Oil Age	hrs	Client Info		2200		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>5	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	2		
Lead	ppm	ASTM D5185m	>65	0		
Copper	ppm	ASTM D5185m	>65	0		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		111		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		72		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	0		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.61		




# **OIL ANALYSIS REPORT**

VISUAL



		VISUAL		method	limit/base	current	history1	history2
		White Metal	scalar	*Visual	NONE	NONE		
		Yellow Metal	scalar	*Visual	NONE	NONE		
		Precipitate	scalar	*Visual	NONE	NONE		
		Silt	scalar	*Visual	NONE	NONE		
		Debris	scalar	*Visual	NONE	NONE		
		Sand/Dirt	scalar	*Visual	NONE	NONE		
	6/23	Appearance	scalar	*Visual	NORML	NORML		
	0ct16/23	Odor	scalar	*Visual	NORML	NORML		
		Emulsified Water	scalar	*Visual	>0.1	NEG		
		Free Water	scalar	*Visual		NEG		
					11.0011/00.0000		In the transmission	la la tana 0
		FLUID PROPERT	IES	method	limit/base	current	history1	history2
		Visc @ 40°C	cSt	ASTM D445		48.7		
		SAMPLE IMAGES	5	method	limit/base	current	history1	history2
	0ct16/23	Color					no image	no image
		Bottom					no image	no image
	шаа	Non-ferrous Metals	5		0et16/23			
		2			0ct16/23			
		40 Abnormal			0.8 0.0 0.0 0.0 0.0 0.0 9 0 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0.0 9 0 0 0 0	10		2
Laborator Sample No Lab Numb Unique Nun tificate 12367 tificate 12367 tificate 12367	o. oer nber age	: 06012574 I : 10751718 I : IND 2	Received Diagnos Diagnos	d : 20 ed : 22 tician : Dor	Nov 2023 Nov 2023 n Baldridge	23160 84TH STREET SW SUITE23BYRON CENTER, M		



Contact/Location: STEPHANIE CLAYPOOL - UCAIRBYR