

## **OIL ANALYSIS REPORT**

#### Area NOT GIVEN Machine Id ATLAS COPCO APF224397 - NTA 8 Component

Compressor

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.






NORMAL

SAMPLE INFORM	<b>NATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06012577		
Sample Date		Client Info		26 Oct 2023		
Machine Age	hrs	Client Info		19052		
Oil Age	hrs	Client Info		3500		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>5	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	2		
Lead	ppm	ASTM D5185m	>65	0		
Copper	ppm	ASTM D5185m	>65	0		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		69		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		135		
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	0		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.44		



# **OIL ANALYSIS REPORT**

VISUAL



		VISUAL		memou			Thistory I	nistory2
	_	White Metal	scalar	*Visual	NONE	NONE		
		Yellow Metal	scalar	*Visual	NONE	NONE		
		Precipitate	scalar	*Visual	NONE	NONE		
		Silt	scalar	*Visual	NONE	NONE		
		Debris	scalar	*Visual	NONE	NONE		
		Sand/Dirt	scalar	*Visual	NONE	NONE		
	0ct26/23	Appearance	scalar	*Visual	NORML	NORML		
	0ct2	Odor	scalar	*Visual	NORML	NORML		
		Emulsified Water	scalar	*Visual	>0.1	NEG		
		Free Water	scalar	*Visual		NEG		
		FLUID PROPERT	IFS	method	limit/base	current	history1	history2
		Visc @ 40°C	cSt	ASTM D445	mmbase	47.5		
					1			
		SAMPLE IMAGES	5	method	limit/base	current	history1	history2
	0ct26/23 + -	Color				aa	no image	no image
		Bottom					no image	no image
	maa	Non-ferrous Metals	S		0ct26/23			
	cSt (40°C)	40 <b>Abnormal</b>			6/23 6/26 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0	Acid Number		
Denotes test methods th	atory : WearCheck USA - 501 Madison Ave., Cary, NC 27513   e No. : UCH06012577 Received : 20 Nov 2023   umber : 06012577 Diagnosed : 22 Nov 2023   Number : 10751721 Diagnostician : Don Baldridge					7513 AIR TECHNOLOGIES INC (GI 160 84TH STREET SW SUITE BYRON CENTER, N US 4931 Contact: STEPHANIE CLAYPOO stephanie.claypool@aircompressors.co		

Contact/Location: STEPHANIE CLAYPOOL - UCAIRBYR