OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Machine Id
ENDEAVOR (S/N 2WB11168)
Component
Starboard Main Engine
Fluid
CHEVRON 15W40 (--- QTS)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0847412**	WC0834549	WC0834566
Sample Date		Client Info		**21 Oct 2023**	14 Aug 2023	06 Jul 2023
Machine Age	hrs	Client Info		**16254**	15682	13761
Oil Age	hrs	Client Info		**94**	300	200
Oil Changed		Client Info		**Not Changd**	N/A	Not Changd
Sample Status				**NORMAL**	NORMAL	ATTENTION

CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	**<1.0**	<1.0	<1.0
Water		WC Method	>0.1	**NEG**	NEG	NEG
Glycol		WC Method		**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>75	**2**	13	6
Chromium	ppm	ASTM D5185m	>8	**0**	<1	0
Nickel	ppm	ASTM D5185m	>2	**0**	0	0
Titanium	ppm	ASTM D5185m	>3	**2**	2	1
Silver	ppm	ASTM D5185m	>2	**0**	0	<1
Aluminum	ppm	ASTM D5185m	>15	**1**	<1	1
Lead	ppm	ASTM D5185m	>18	**0**	1	<1
Copper	ppm	ASTM D5185m	>80	**<1**	<1	<1
Tin	ppm	ASTM D5185m	>14	**<1**	0	0
Vanadium	ppm	ASTM D5185m		**<1**	<1	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**68**	285	342
Barium	ppm	ASTM D5185m		**0**	0	1
Molybdenum	ppm	ASTM D5185m		**19**	81	81
Manganese	ppm	ASTM D5185m		**<1**	<1	0
Magnesium	ppm	ASTM D5185m		**167**	485	381
Calcium	ppm	ASTM D5185m		**2119**	1778	1664
Phosphorus	ppm	ASTM D5185m		**974**	1134	1056
Zinc	ppm	ASTM D5185m		**1183**	1450	1233
Sulfur	ppm	ASTM D5185m		**3851**	4293	3498

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	**6**	5	3
Sodium	ppm	ASTM D5185m	>50	**<1**	2	0
Potassium	ppm	ASTM D5185m	>20	**3**	3	2

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		**0**	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	**6.3**	8.4	6.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	**17.1**	21.8	20.5

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**11.3**	18.5	15.9
Base Number (BN)	mg KOH/g	ASTM D2896		**7.6**	8.58	9.19

OIL ANALYSIS REPORT









VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	**13.13**	13.9	▲ 13.57

GRAPHS









Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0847412 **Recieved** : 20 Nov 2023
Lab Number : 06012602 **Diagnosed** : 29 Nov 2023
Unique Number : 10751746 **Diagnostician** : Jonathan Hester
Test Package : MAR 2 (Additional Tests: KV40)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CITY EXPERIENCES - SEAWARD EXPLORER
2825 5TH AVENUE
SAN DIEGO, CA
US 92103
Contact: PETER CHARBONNET

T: (985)290-6777
F: