

## **OIL ANALYSIS REPORT**

Sample Rating Trend



NORMAL

CATERPILLAR RH BEYMER Component

**Starboard Genset** Fluid

KENDALL SUPER-D XA 15W40 (--- GAL)

DIAGNOSIS	SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Recommendation	Sample Number		Client Info		WC0843975	WC0843985	
Resample at the next service interval to monitor.	Sample Date		Client Info		15 Nov 2023	19 Sep 2023	
Wear	Machine Age	hrs	Client Info		17828	17187	
All component wear rates are normal.	Oil Age	hrs	Client Info		250	500	
Contamination	Oil Changed		Client Info		Changed	Changed	
There is no indication of any contamination in the	Sample Status				NORMAL	NORMAL	
oil.	CONTAMINATION		method	limit/base	ou www.opt		history2
Fluid Condition		N			current	history1	
The BN result indicates that there is suitable	Fuel		WC Method	>4.0	<1.0	<1.0	
alkalinity remaining in the oil. The condition of the	Water		WC Method	>0.1	NEG	NEG	
oil is suitable for further service.	Glycol		WC Method		NEG	NEG	
	WEAR METALS		method	limit/base	current	history1	history2
	Iron	ppm	ASTM D5185m	>50	9	10	
	Chromium	ppm	ASTM D5185m	>4	<1	0	
	Nickel	ppm	ASTM D5185m	>2	<1	0	
	Titanium	ppm	ASTM D5185m		49	33	
	Silver	ppm	ASTM D5185m	>5	0	0	
	Aluminum	ppm	ASTM D5185m	>12	2	<1	
	Lead	ppm	ASTM D5185m	>17	<1	<1	
	Copper	ppm	ASTM D5185m	>70	1	<1	
	Tin	ppm	ASTM D5185m	>15	0	<1	
	Vanadium	ppm	ASTM D5185m		<1	0	
	Cadmium	ppm	ASTM D5185m		<1	0	
	ADDITIVES		method	limit/base	current	history1	history2
	Boron	ppm	ASTM D5185m	50	81	49	
	Barium	ppm	ASTM D5185m		9	0	
	Molybdenum	ppm	ASTM D5185m		34	36	
	Manganese	ppm	ASTM D5185m		<1	<1	
	Magnesium	ppm	ASTM D5185m	270	252	212	
	Calcium	ppm	ASTM D5185m	1900	2110	2311	
	Phosphorus	ppm	ASTM D5185m	1000	1015	982	
	Zinc	ppm	ASTM D5185m	1260	1183	1276	
	Sulfur	ppm	ASTM D5185m	3400	3939	3813	
	CONTAMINANTS		method	limit/base	current	history1	history2
	Silicon	ppm	ASTM D5185m	>25	4	3	
	Sodium	ppm	ASTM D5185m		<1	2	
	Potassium	ppm	ASTM D5185m	>20	4	1	
	INFRA-RED		method	limit/base	current	history1	history2
	Soot %	%	*ASTM D7844		0.1	0.1	
	Nitration	Abs/cm	*ASTM D7624	>20	10.3	10.4	
	Sulfation	Abs/.1mm	*ASTM D7415		20.6	20.9	
	FLUID DEGRADA		method	limit/base	current	history1	history2
	Oxidation	Abs/.1mm	*ASTM D7414		18.2	18.1	
						7.3	
	Dase Nulliber (DN)	niy KOH/g	ASTM D2896	9.0	7.7	1.5	



## **OIL ANALYSIS REPORT**

