

OIL ANALYSIS REPORT

Juc2017 Oct2011 Nex2018 Nex2018 Nex2021 Nex2022 Nex2022

Sample Rating Trend



NORMAL

KAESER ASD 40T 5555915 (S/N 1167)

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA009269	KCP47651D	KCP43093
Sample Date		Client Info		08 Nov 2023	22 Nov 2022	16 Nov 2021
Machine Age	hrs	Client Info		23495	20440	17043
Oil Age	hrs	Client Info		0	3397	4300
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	<1
Chromium	ppm	ASTM D5185m	>10	0	<1	<1
Nickel	ppm	ASTM D5185m	>3	<1	0	<1
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	1	<1
Aluminum	ppm	ASTM D5185m	>10	۰ <1	1	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	8	11	9
Tin	ppm	ASTM D5185m	>10	۰ <1	<1	<1
Antimony	ppm	ASTM D5185m	- 10			0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	ppiii		11 14 10	-	-	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	16
Barium	ppm	ASTM D5185m	90	0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	90	28	26	42
Calcium	ppm	ASTM D5185m	2	1	0	0
Phosphorus	ppm	ASTM D5185m		1	2	4
Zinc	ppm	ASTM D5185m		65	39	47
Sulfur	ppm	ASTM D5185m		18138	19455	17405
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	0
Sodium	ppm	ASTM D5185m		10	9	16
Potassium	ppm	ASTM D5185m		1	3	4
Water	%	ASTM D6304	>0.05	0.011	0.012	0.016
ppm Water	ppm	ASTM D6304	>500	115.0	126.4	160.1
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		2465	18133	2143
Particles >6µm		ASTM D7647	>1300	713	6 748	414
Particles >14µm		ASTM D7647	>80	39	4 70	35
Particles >21µm		ASTM D7647	>20	8	<u> </u>	9
Particles >38µm		ASTM D7647	>4	0	3	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	18/17/12	1 /20/16	16/12
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.34	0.42	0.402
25:58) Rev: 1 Contact/Location: SERV/ICE MANAGER 2 - TTRLOU						


Report Id: TTRLOU [WUSCAR] 06013366 (Generated: 11/22/2023 21:25:58) Rev: 1


Contact/Location: SERVICE MANAGER ? - TTRLOU



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.1	44.4	44.3
SAMPLE IMAGES	\$	method	limit/base	current	history1	history2
Color						

