


OIL ANALYSIS REPORT

Sample Rating Trend



KAESER 7171473 Component Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA007686	KCPA003300	KCP55925
Sample Date		Client Info		16 Nov 2023	20 Jun 2023	08 Feb 2023
Machine Age	hrs	Client Info		16073	16431	10823
Oil Age	hrs	Client Info		0	0	3584
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	ATTENTION	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm		>50	0	0	0
Chromium	ppm	ASTM D5185m		0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	2	0
Lead		ASTM D5185m	>10	0	0	0
Copper	ppm ppm		>50	4	2	6
Tin	ppm	ASTM D5185m	>50	4 <1	0	0
Vanadium	ppm	ASTM D5185m	>10	0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	ррш		11 1. 0		-	-
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	4	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	90	9	19	<1
Calcium	ppm	ASTM D5185m	2	1	0	0
Phosphorus	ppm	ASTM D5185m		1	0	7
Zinc	ppm	ASTM D5185m		7	9	0
Sulfur	ppm	ASTM D5185m		17818	19236	22095
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	1
Sodium	ppm	ASTM D5185m		4	5	<1
Potassium	ppm	ASTM D5185m	>20	0	<1	0
Water	%	ASTM D6304		0.006	0.013	0.003
ppm Water	ppm	ASTM D6304	>500	69.8	138.9	37.3
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		2533	4544	1352
Particles >6µm		ASTM D7647	>1300	691	<u> </u>	339
Particles >14µm		ASTM D7647	>80	61	71	13
Particles >21µm		ASTM D7647		19	20	1
Particles >38µm		ASTM D7647	>4	2	1	0
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	19/17/13	▲ 19/18/13	18/16/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.34	0.37	0.39


Contact/Location: Service Manager - AMAGAR



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	LIGHT	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	45.6	44.8	48.4
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				•		
					1	

Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: Service Manager - AMAGAR