


OIL ANALYSIS REPORT

Sample Rating Trend





Machine Id **1714** Component **Diesel Engine**

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | Mar2022 May2 | 022 Aug2022 Dec2022 Jan2 | 023 Feb2023 Apr2023 Jun2023 Sep | 2023 Oct2023 | |
|------------------|----------|--------------|--------------------------|---------------------------------|--------------|-------------|
| SAMPLE INFORI | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | WC0860381 | WC0844987 | WC0827060 |
| Sample Date | | Client Info | | 30 Oct 2023 | 07 Sep 2023 | 30 Jun 2023 |
| Machine Age | mls | Client Info | | 206282 | 0 | 195117 |
| Oil Age | mls | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | Changed | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 5 | 9 | 6 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 3 | 3 | 2 |
| Lead | ppm | ASTM D5185m | >40 | <1 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >330 | 4 | 2 | 2 |
| Tin | ppm | ASTM D5185m | >15 | 0 | <1 | <1 |
| Vanadium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 250 | 125 | 18 | 18 |
| Barium | ppm | ASTM D5185m | | 0 | 2 | 2 |
| Molybdenum | ppm | ASTM D5185m | 100 | 71 | 84 | 74 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | | 323 | 262 | 277 |
| Calcium | ppm | ASTM D5185m | | 1390 | 2126 | 2078 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 888 | 1146 | 1094 |
| Zinc | ppm | ASTM D5185m | | 1131 | 1398 | 1361 |
| Sulfur | ppm | ASTM D5185m | | 3005 | 3918 | 4313 |
| CONTAMINANTS | S | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 8 | 11 | 6 |
| Sodium | ppm | ASTM D5185m | >158 | 7 | 10 | 8 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 1 | 1 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.3 | 0.4 | 0.3 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 9.5 | 10.8 | 10.4 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 22.1 | 22.0 | 21.6 |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 20.0 | 19.8 | 18.8 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 5.6 | 5.9 | 6.0 |
| | | | | | | |



OIL ANALYSIS REPORT








| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |


| FLUID PROPERTIES | | method | | | | history2 |
|------------------|-----|-----------|------|------|------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 13.3 | 14.0 | 13.7 |

GRAPHS













Laboratory Sample No. Lab Number Test Package : FLEET

Unique Number

: WC0860381 : 06013778 : 10752922

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 21 Nov 2023 Diagnosed : 22 Nov 2023 Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

US 27516 Contact: Lisa DePasqua Idepasqua@townofchapelhill.org

T: (919)696-4941

TOWN OF CHAPEL HILL

6900 MILLHOUSE RD

CHAPEL HILL, NC

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)