

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

FRICK RC 7 (S/N SGC23170260)

Refrigeration Compressor

FRICK COMPRESSOR OIL #3 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Jun2018	Jul2019 Jun2020	Jul2021 Jul2022	Aug2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP230322	USP230327	USP202070
Sample Date		Client Info		24 Aug 2023	21 Jul 2022	24 Jul 2021
Machine Age	hrs	Client Info		0	71128	64050
Oil Age	hrs	Client Info		0	71128	64050
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	<1	2	1
Chromium	ppm	ASTM D5185m	>2	<1	0	0
Nickel	ppm	ASTM D5185m		<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m		0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	<1
Copper	ppm	ASTM D5185m		<1	0	0
Tin	ppm	ASTM D5185m	>4	0	<1	<1
Antimony	ppm	ASTM D5185m	~ 1			0
Vanadium		ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0 <1	0	0
	ppm	MCQ1C0 INLOW		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		0	0	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		0	0	0
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		285	416	371
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2	2	<1
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
Water	%	ASTM D6304		0.003	0.001	0.002
ppm Water	ppm	ASTM D6304	>100	27	13.2	15.1
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	1219	421	4851
Particles >6µm		ASTM D7647	>2500	234	95	805
Particles >14µm		ASTM D7647	>320	10	6	19
Particles >21µm		ASTM D7647	>80	3	2	2
Particles >38µm		ASTM D7647	>20	0	0	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	17/15/10	16/14/10	19/17/11
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974		0.014	0.014	0.015
:08:48) Rev: 1		Contact/Location: KRIS STOVER - SCHSTETX				


Report Id: SCHSTETX [WUSCAR] 06014088 (Generated: 11/24/2023 09:08:48) Rev: 1


Contact/Location: KRIS STOVER - SCHSTETX



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	73	68.3	69.4	67.5
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color						

Bottom



Contact/Location: KRIS STOVER - SCHSTETX