

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area SMART OIL 6000 Machine Id HERTZ VD032285 - SHOP Component

Compressor Fluid

SMARTOIL 6000 (5 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Nov2023		
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06014115		
Sample Date		Client Info		07 Nov 2023		
Machine Age	hrs	Client Info		12560		
Oil Age	hrs	Client Info		2000		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m	20	<1		
Phosphorus	ppm	ASTM D5185m		41		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		317		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.09		



OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual	>0.1	NEG		
Fiee Water	Scalal	VISUAI		NEG		
FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.8		
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color					no image	no image
Bottom				\bigcirc	no image	no image
GRAPHS Ferrous Alloys			Nov7/23			
Non-ferrous Meta	ls		N N			
Viscosity @ 40°C			1.0 0.0 0.0 (m 0.0 (m 0.0 V)/23 0.0 Vortigion 0.0 Vortigio	Acid Number		- EZ/IVON
: 06014115	Received Diagnose Diagnost	d : 21 ed : 24 iician : Dou	Nov 2023 Nov 2023 ug Bogart	3	5723 WEATHE JC	OR SERVICES RSTONE WAY DHNSBURG, IL US 60051 ICHAEL BRITT

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory

Sample No. Lab Number Unique Number Test Package

T: (847)497-9750

F: (847)497-9754