



# OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id

## TOTE 2

Component

### New (Unused) Oil

Fluid

{not provided} (--- GAL)

#### DIAGNOSIS

##### ▲ Recommendation

This is a baseline read-out on the submitted sample.

##### ▲ Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

#### SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC06014387</b>	---	---
Sample Date	Client Info		<b>20 Nov 2023</b>	---	---
Machine Age	hrs	Client Info	<b>0</b>	---	---
Oil Age	hrs	Client Info	<b>0</b>	---	---
Oil Changed	Client Info		<b>N/A</b>	---	---
Sample Status			<b>ABNORMAL</b>	---	---

#### WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	<b>0</b>	---	---
Chromium	ppm	ASTM D5185m	<b>0</b>	---	---
Nickel	ppm	ASTM D5185m	<b>0</b>	---	---
Titanium	ppm	ASTM D5185m	<b>0</b>	---	---
Silver	ppm	ASTM D5185m	<b>0</b>	---	---
Aluminum	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Lead	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Copper	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Tin	ppm	ASTM D5185m	<b>0</b>	---	---
Vanadium	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Cadmium	ppm	ASTM D5185m	<b>0</b>	---	---

#### ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	<b>0</b>	---	---
Barium	ppm	ASTM D5185m	<b>0</b>	---	---
Molybdenum	ppm	ASTM D5185m	<b>0</b>	---	---
Manganese	ppm	ASTM D5185m	<b>0</b>	---	---
Magnesium	ppm	ASTM D5185m	<b>0</b>	---	---
Calcium	ppm	ASTM D5185m	<b>101</b>	---	---
Phosphorus	ppm	ASTM D5185m	<b>296</b>	---	---
Zinc	ppm	ASTM D5185m	<b>457</b>	---	---
Sulfur	ppm	ASTM D5185m	<b>1081</b>	---	---

#### CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	<b>4</b>	---	---
Sodium	ppm	ASTM D5185m	<b>2</b>	---	---
Potassium	ppm	ASTM D5185m	<b>&gt;20</b>	---	---
Water	%	ASTM D6304	<b>NEG</b>	---	---

#### FLUID CLEANLINESS





	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		<b>83593</b>	---	---
Particles >6µm	ASTM D7647	>1300	<b>▲ 8357</b>	---	---
Particles >14µm	ASTM D7647	>160	<b>160</b>	---	---
Particles >21µm	ASTM D7647	>40	<b>44</b>	---	---
Particles >38µm	ASTM D7647	>10	<b>1</b>	---	---
Particles >71µm	ASTM D7647	>3	<b>0</b>	---	---
Oil Cleanliness	ISO 4406 (c)	>--/17/14	<b>▲ 24/20/14</b>	---	---

#### FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	<b>0.30</b>	---	---



# OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	NEG	---	---
Free Water	scalar	*Visual	NEG	---	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	67.76	---	---
Visc @ 100°C	cSt	ASTM D445	11.29	---	---
Viscosity Index (VI)	Scale	ASTM D2270	160	---	---

### SAMPLE IMAGES

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

### GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC06014387 **Received** : 21 Nov 2023  
**Lab Number** : 06014387 **Diagnosed** : 27 Nov 2023  
**Unique Number** : 10753531 **Diagnostician** : Jonathan Hester  
**Test Package** : MOB 2 ( Additional Tests: FT-IR, ICP-NewOil, KF, KV100, PrtCount, VI )

**SAMPSON-BLADEN OIL COMPANY, INC.**  
 PO BOX 469  
 CLINTON, NC  
 US 28329  
 Contact: BOB FAIRCLOTH  
 bob.faircloth@sampsonbladen.com  
 T: (800)341-9266  
 F: (910)596-0206

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)