
PROBLEM SUMMARY



Area **EBAY** Machine Id **SB13MGB** Component **Gearbox** Fluid

GEAR OIL ISO 320 (--- GAL)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

Resample at the next service interval to monitor. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.

PROBLEMATIC TEST	RESULTS			
Sample Status		ATTENTION	ATTENTION	ATTENTION
Particles >4µm	ASTM D7647 >4000) 🔺 55288	▲ 50069	60333
Oil Cleanliness	ISO 4406 (c) >22/19	/16 🔺 23/19/13	🔺 23/19/13	a 23/20/14


Customer Id: KOBPIN Sample No.: ST46008 Lab Number: 06014538 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Don Baldridge +1 <u>don.b505@comcast.net</u>

To change component or sample information: Customer Service +1 1-800-237-1369 <u>customerservice@wearcheck.com</u>



RECOMMENDED	ACTIONS			
Action	Status	Date	Done By	C
Contact Required			?	C (2

Description

Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.

HISTORICAL DIAGNOSIS



03 Nov 2023 Diag: Don Baldridge

Resample at the next service interval to monitor. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.All component wear rates are normal. There is a moderate amount of silt (particulates < 6 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



view report

22 Jun 2023 Diag: Doug Bogart



Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



23 May 2023 Diag: Jonathan Hester

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.All component wear rates are normal. There is a high amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT



Fluid GEAR OIL ISO 320 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 6 microns in size) present in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


Sample Rating Trend ISO


		and the state	Pres 10 /le se se s		In the term of the	history O
SAMPLE INFORM	/IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ST46008	ST46007	ST44487
Sample Date		Client Info		16 Nov 2023	03 Nov 2023	22 Jun 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Sample Status				ATTENTION	ATTENTION	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	13	13	10
Chromium	ppm	ASTM D5185m	>15	<1	0	<1
Nickel	ppm	ASTM D5185m	>15	<1	0	<1
Titanium	ppm	ASTM D5185m		1	<1	2
Silver	ppm	ASTM D5185m		0	0	_ <1
Aluminum	ppm	ASTM D5185m	>25	2	0	0
Lead	ppm	ASTM D5185m	>100	- <1	0	2
Copper	ppm	ASTM D5185m	>200	<1	0	<1
Tin	ppm		>25	0	0	<1
Vanadium	ppm	ASTM D5185m	~20	0	0	<1
Cadmium	ppm	ASTM D5185m		۰ <1	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	17	13	12
Barium	ppm	ASTM D5185m	15	0	0	0
Molybdenum	ppm	ASTM D5185m	15	<1	0	<1
Manganese	ppm	ASTM D5185m	10	<1	0	<1
Magnesium	ppm	ASTM D5185m	50	<1	0	<1
Calcium	ppm	ASTM D5185m	50	27	28	20
Phosphorus	ppm	ASTM D5185m	350	310	300	210
Zinc	ppm	ASTM D5185m	100	0	12	0
Sulfur	ppm	ASTM D5185m	12500	19976	17620	15801
CONTAMINANTS		method	limit/base			
				current	history1	history2
Silicon	ppm	ASTM D5185m	>50	1	0	<1
Sodium	ppm	ASTM D5185m	00	0	0	<1
Potassium	ppm	ASTM D5185m	>20	2	<1	3
Water	%	ASTM D6304		0.013	0.007	0.006
ppm Water	ppm	ASTM D6304	>2000	138	77.8	61.1
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>40000	▲ 55288	▲ 50069	▲ 60333
Particles >6µm		ASTM D7647	>5000	4818	3914	<u>▲</u> 6681
Particles >14µm		ASTM D7647	>640	76	43	119
Particles >21µm		ASTM D7647	>160	16	9	18
Particles >38µm		ASTM D7647	>40	1	0	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>22/19/16	A 23/19/13	2 3/19/13	▲ 23/20/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	0.59	0.66	0.71




OIL ANALYSIS REPORT











VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	314	316	316
SAMPLE IMAGE	S	method	limit/base	current	history1	history2

Color



Bottom



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: NEAL SHINAULT - KOBPIN

F:

T: (336)604-1498