

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area SMART OIL 6000 Machine Id HERTZ VD012910 - AMCOR Component

Compressor

SMARTOIL 6000 (--- GAL)

DIAGNOSIS

Recommendation

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Oct2023		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06015262		
Sample Date		Client Info		13 Oct 2023		
Machine Age	hrs	Client Info		6357		
Oil Age	hrs	Client Info		2784		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m	20	0		
Phosphorus	ppm	ASTM D5185m		32		
Zinc	ppm	ASTM D5185m		17		
Sulfur	ppm	ASTM D5185m		103		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.25		




44 42. Abnormal 40 0ct13/23

Ò

۵S# с.

OIL ANALYSIS REPORT

VISUAL



	White Metal						
		scalar	*Visual	NONE	LIGHT		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate		*Visual	NONE	NONE		
	Silt		*Visual	NONE	NONE		
	Debris		*Visual	NONE	MODER		
	Sand/Dirt		*Visual	NONE	NONE		
			*Visual	NORML	NORML		
0.413.073	Odor		*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.1	NEG		
				>0.1			
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	46	46.4		
	SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
0.e43.02	Color					no image	no image
	Bottom			(no image	no image
	Non-ferrous Meta	als		0ct13/23			
	Non-ferrous Meta			0ct13/23	Acid Number		
	Non-ferrous Meta						
Laboratory Sample No. Lab Number Unique Number Test Package	Non-ferrous Meta Non-ferrous Meta Copper Ind Viscosity @ 40°C Viscosity @ 40°C State Copper Viscosity @ 40°C State Copper Ind Copper In	501 Madise Received Diagnose Diagnostie	: 22 M d : 26 M cian : Don	C2CEEtP0 (0,10,0,3) (0,10,0,2) (0,10,0,1) (0,10,0,	3 MADDO	X AIR COMPRI 951 PENNSYL KENT@MAI	

Contact/Location: KENT ? - UCMADOGD