

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id Shag 12 Component Diesel Engine Fluid NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0006288		
Sample Date		Client Info		16 Nov 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	25		
Chromium	ppm	ASTM D5185m	>20	1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m	- 1	0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	11		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	2		
Tin	ppm	ASTM D5185m	>15	- <1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		17		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		32		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		177		
Calcium	ppm	ASTM D5185m		2107		
Phosphorus	ppm	ASTM D5185m		935		
Zinc	ppm	ASTM D5185m		1136		
Sulfur	ppm	ASTM D5185m		3409		
CONTAMINANTS		method	limit/base	current	history1	history2
		ASTM D5185m				
Silicon Sodium	ppm ppm	ASTM D5185m	>25	10 3		
Potassium	ppm	ASTM D5185m	>20	3		
	ppm					
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7		
Nitration	Abs/cm	*ASTM D7624	>20	10.1		
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.2		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.8		
Base Number (BN)	mg KOH/g	ASTM D2896		6.3		



OIL ANALYSIS REPORT

Non-ferrous Metals

Viscosity @ 100°C

10

18

16

13

12

11

Laboratory Sample No.

Lab Number


Nov16/23

: SBP0006288

: 06015698

cSt (100°C)

Base Number 7.0 6.0 (B/H03) 5.0 Ë 4.0 년 3.0 2.0 1.0 0.0 Jov16/23 Nov16/23 Viscosity @ 100°C





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445		13.8		
GRAPHS						
Ferrous Alloys						
25 iron						
20 - nickel						
15-						
10-						

Jov16/7

Nov16/23 -

: 22 Nov 2023

: 26 Nov 2023

7.0 6. (B/HO)

E 4.0 e 3.0

器 2.0

1.0

0.0

Nov16/23

Base Number



Unique Number : 10754842 Diagnostician : Wes Davis Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. troyfr@pillenfamilyfarms.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Pillen Family Farms - 722828

16/23

F:

26741 NE-91

Humphrey, NE

Contact: Troy Runge

T: (308)390-6733

US 61357