

Sample Rating Trend

NORMAL



## Machine Id Component Wind Turbine Gearbox **ROYAL PURPLE SYNFILM GT 320 (65 GAL)**

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

Flui

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

		Apr201	2 Apr2020	Feb2022	Apr2023	
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		MHI021613	MHI019862	MHI022642
Sample Date		Client Info		25 Apr 2023	13 Feb 2022	23 Apr 2020
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	109268
Oil Changed		Client Info		N/A	N/A	Not Changd
Sample Status				NORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184	>200	12	15	22
Iron	ppm	ASTM D5185m	>200	25	19	8
Chromium	ppm	ASTM D5185m	>3	<1	0	<1
Nickel	ppm	ASTM D5185m	>3	0	<1	0
Titanium	ppm	ASTM D5185m	>10	<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm		>30	2	0	0
Lead	ppm		>15	0	0	0
Copper	ppm	ASTM D5185m	>75	16	10	8
Tin	ppm		>10	0	0	<1
Antimony	ppm	ASTM D5185m	>5		0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	ppin			-	-	-
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	<1	<1
Barium	ppm	ASTM D5185m		0	0	<1
Molybdenum	ppm	ASTM D5185m		4	3	3
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	90	<1	0	0
Calcium	ppm	ASTM D5185m		0	0	<1
Phosphorus	ppm	ASTM D5185m		211	176	173
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		17260	8522	6083
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+30	<1	1	1
Sodium	ppm	ASTM D5185m		0	0	1
Potassium	ppm	ASTM D5185m	>20	2	0	0
Water	%	ASTM D6304	>0.1	0.008	0.004	0.004
ppm Water	ppm	ASTM D6304	>1000	83	43.0	41.2
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		17845	217293	11821
Particles >6µm		ASTM D7647	>5000	569	🔺 151786	448
Particles >14µm		ASTM D7647	>640	7	<b>A</b> 20360	11
Particles >21µm		ASTM D7647		4	▲ 2027	3
Particles >38µm		ASTM D7647		1	▲ 45	0
Particles >71µm		ASTM D7647		1	2	0
			-	-		
Oil Cleanliness		ISO 4406 (c)	>/19/16	21/16/10	▲ 25/24/22	21/16/11



Water (KF)

Feb 13/22

eb13/22

eb13/22

Feb13/22

or25/23

pr25/23

> > Particle Trend

Viscosity @ 40°C

wr23/20

5 100

Ok

400 380

360

() 340 0€ 320

200 25 300

280 260 Al

240.

400 350 300

250

립200

150

100 50 Inr2/1

PQ

Cur?

# **OIL ANALYSIS REPORT**

FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.25	0.70	0.70	0.788
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	326	330	319
SAMPLE IMAGES		method	limit/base	current	history1	history2





60

20

400

Color



