


SAMPLE INFORMATION method

Sample Rating Trend





NORMAL

H-04 Component Hydraulic System
Fluid MOBIL DTE 10 EXCEL 32 (45 GAL)

DIAGNOSIS

DIAMOND WTG

ENGINEERING & SERVICES, INC.

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		MHI021615	MHI019353	MHI022617
Sample Date		Client Info		11 May 2023	22 Jul 2021	08 May 2020
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	114623
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL
WEAR METALS		mathad	limit/bass	ourroot	biotomat	biotory
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	23	16	11
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>20	1	1	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	0	0
Lead	ppm	ASTM D5185m	>20	<1	<1	<1
Copper	ppm	ASTM D5185m	>20	<1	<1	<1
Tin	ppm	ASTM D5185m	>20	0	0	0
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		3	1	3
Calcium	ppm	ASTM D5185m	120	132	135	124
Phosphorus	ppm	ASTM D5185m	475	424	479	448
Zinc	ppm	ASTM D5185m		15	13	16
Sulfur	ppm	ASTM D5185m	1275	1770	1398	1400
CONTAMINANTS	\$	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+30	<1	<1	2
Sodium	ppm	ASTM D5185m		0	2	2
Potassium	ppm	ASTM D5185m	>20	1	0	0
Water	%	ASTM D6304	>0.1	0.012	0.041	0.002
ppm Water	ppm	ASTM D6304	>1000	121	412.4	22.3
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	729	2 6913	1863
Particles >6µm		ASTM D7647		193	<u> </u>	366
Particles >14µm		ASTM D7647	>160	50	<u>▲</u> 623	30
Particles >21µm		ASTM D7647	>40	25	<u> </u>	7
Particles >38µm		ASTM D7647	>10	2	3	0
Particles >71µm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/15/13	▲ 22/20/16	18/16/12
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.154	0.04	0.108
34:38) Rev: 1	- 0		Co	ntact/Location:	WESLEY CAMP	BELL - MITWI


Report Id: MITWHI [WUSCAR] 06016375 (Generated: 11/29/2023 19:34:38) Rev: 1


Contact/Location: WESLEY CAMPBELL - MITWHI


Page 1 of 2



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	VLITE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	32	33.4	32.4	32.2
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						

Bottom

