




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
FREIGHTLINER 2422
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON HP 15W40 (17 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		RW0004656	RW0003929	RW0002982
Sample Date	Client Info		26 Oct 2023	22 Nov 2022	30 Mar 2022
Machine Age	hrs	Client Info	8562	7545	6691
Oil Age	hrs	Client Info	768	610	500
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >130	41	31	24
Chromium	ppm	ASTM D5185m >10	2	1	1
Nickel	ppm	ASTM D5185m >4	<1	0	0
Titanium	ppm	ASTM D5185m >2	<1	<1	2
Silver	ppm	ASTM D5185m >2	0	<1	<1
Aluminum	ppm	ASTM D5185m >20	10	6	5
Lead	ppm	ASTM D5185m >20	<1	0	<1
Copper	ppm	ASTM D5185m >125	3	1	2
Tin	ppm	ASTM D5185m >4	1	<1	<1
Antimony	ppm	ASTM D5185m	---	---	---
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	17	137	9
Barium	ppm	ASTM D5185m	0	0	0
Molybdenum	ppm	ASTM D5185m	73	81	62
Manganese	ppm	ASTM D5185m	<1	<1	<1
Magnesium	ppm	ASTM D5185m	232	377	947
Calcium	ppm	ASTM D5185m	1902	1505	1190
Phosphorus	ppm	ASTM D5185m	1064	1035	1099
Zinc	ppm	ASTM D5185m	1216	1230	1229
Sulfur	ppm	ASTM D5185m	3441	3705	2781

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	10	5	5
Sodium	ppm	ASTM D5185m	3	0	0
Potassium	ppm	ASTM D5185m >20	15	10	0

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	1.4	1.3	0.5
Nitration	Abs/cm	*ASTM D7624 >20	13.0	11.4	10.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	27.5	27.5	25.1

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	22.2	21.5	18.3
Base Number (BN)	mg KOH/g	ASTM D2896 9.8	5.78	5.24	7.09











OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.6	13.3	13.5	13.5

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : RW0004656
 Lab Number : 06016668
 Unique Number : 10755812
 Test Package : MOB 2

Received : 24 Nov 2023
 Diagnosed : 28 Nov 2023
 Diagnostician : Sean Felton

NEWKIRK ELECTRIC
 1875 ROBERTS ST.
 MUSKEGON, MI
 US 49442

Contact: ERIC KING
 ewking@newkirk-electric.com
 T: (231)206-6131
 F: (231)724-4090

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)