

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

NOT GIVEN WC0862686 [] Component

Transmission Fluic NOT GIVEN (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.

			11 11 11			
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0862686		
Sample Date		Client Info		05 Dec 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	30		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>50	2		
Lead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m	>200	5		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		7		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		15		
Calcium	ppm	ASTM D5185m		2908		
Phosphorus	ppm	ASTM D5185m		1032		
Zinc	ppm	ASTM D5185m		1250		
Sulfur	ppm	ASTM D5185m		6068		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	5		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
2:14:39) Rev: 1				0		KING - SHEWIC



OIL ANALYSIS REPORT



	FLUID PROPER	RTIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		95.7		
	SAMPLE IMAG	ES	method	limit/base	current	history1	history2
23 -	Color				no image	no image	no image
Dec5/23	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys			_			
	25 - iron mickel						
	20-						
Maa	15-						
	10-						
	5-						
	Dec5/23			Dec5/23			
	□ Non-ferrous Met	als		Ω			
	9 copper						
	8						
	6-						
-	4						
	2						
				- 123			
	Dec5/23			Dec5/23			
	Viscosity @ 40°C	C 					
	100						
C	98						
cSt (40°C)	94						
	90						
	86 84 - Abnormal						
	82 + Dec2/33			Dec5/23 +			
	WearCheck USA WC0862686 06026899 10776690 CONST ontact Customer Se.	ed : 06 D sed : 08 D stician : Jona	SHERWOOD CONSTRUCTION CO INC 3219 WEST MAY ST WICHITA, KS US 67213 Contact: DOUG KING doug.king@sherwood.nei				
t methods that ar	re outside of the ISO fications are based or	17025 sc	ope of accredi	tation.	JCGM 106:2012	T:	(316)617-316 F: >

Contact/Location: DOUG KING - SHEWIC