

OIL ANALYSIS REPORT

Sample Rating Trend





CATERPILLAR 745D 13403 (S/N 3T606051)

Transmission (Manual)

TDTO FLUID SAE 30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition


The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0863010		
Sample Date		Client Info		27 Nov 2023		
Machine Age	hrs	Client Info		567		
Oil Age	hrs	Client Info		567		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	13		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m	>5	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>7	0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>45	<1		
Copper	ppm	ASTM D5185m	>225	14		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	37	0		
Barium	ppm	ASTM D5185m	7	0		
Molybdenum	ppm	ASTM D5185m	5	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	40	7		
Calcium	ppm	ASTM D5185m	2650	3097		
Phosphorus	ppm	ASTM D5185m	1050	1044		
Zinc	ppm	ASTM D5185m	1075	1233		
Sulfur	ppm	ASTM D5185m	5750	8096		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>125	7		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
A	scalar	*Visual	NORML	NORML		
Appearance	Scalal	VISUUI				
	scalar	*Visual	NORML	NORML		
Odor						



OIL ANALYSIS REPORT

FLUID PROPERTIES method limit/base



	Visc @ 40°C	cSt	ASTM D445	101	83.1	nistory i	nistory2
	SAMPLE IMAG		method	limit/base	current	history1	history2
23	Color				no image	no image	no image
Nov27/23	Bottom				no image	no image	no image
	GRAPHS						
	Ferrous Alloys			1/33			
	Non-ferrous Met	als		Nov27/22			
	2 0 Viscosity @ 40°C	*****		Nov27/23			
1 JANUP 1 AV	105 Base Base 3 95 90 Abnormal 85						
d Laboratory	: WearCheck USA				3 Т	RADER CONST	
Certificate L2367 To discuss this sample report, of the statements of conformity to specific	are outside of the ISO	17025 sco	ed : 08 [tician : Don 300-237-1369 ope of accred	itation.		N Contact wyatt@tradercc T:	DRAWER 1578 EW BERN, NC US 28563 MIKE WYATT onstruction.com (252)633-1399 (252)638-4871

Ĕ

Contact/Location: MIKE WYATT - TRANEW