


COOLANT REPORT

FRONTIER II [200006776] Machine Id 54WEA86923

Component

Coolant

ISENTHAL VARIDOS 45 (--- LTR)





DIAGNOSIS

Recommendation

The fluid is suitable for further service.

Corrosion

All metal levels are normal indicating no corrosion in the cooling system.

Contaminants

There is no indication of any contamination in the coolant.


Coolant Condition

Glycol and nitrite levels are acceptable. The pH level of this fluid is within the acceptable limits.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		NX06027000	NX05868409	NX05487232
Sample Date		Client Info		22 Nov 2023	27 Apr 2023	23 Feb 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	0	Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	SEVERE
			11. 11.0			
PHYSICAL TEST R	RESULTS	method	limit/base	current	history1	history2
Specific Gravity		*ASTM D1298		1.060	1.060	1.055
рН	Scale 0-14	ASTM D1287		7.77	8.29	8.41
Nitrites	ppm	AP-053:2009	260	372	336	0
Reserve Alkalinity	Scale 0-20	*ASTM D1121				
Percentage Glycol	%	ASTM D3321	45	44.8	44.3	40.8
Freezing Point	°F	ASTM D3321	-24	-21	-21	-13
Total Dissolved Solids				242.5	153.0	176.5
Carboxylate				n/a	n/a	fail
CORROSION INH	IBITORS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D6130	25	10	0	74
Phosphorus	ppm	ASTM D6130	140	<1	0	174
Boron	ppm	ASTM D6130	0	0	0	0
Molybdenum	ppm	ASTM D6130	1075	0	229	1077
CORROSION		method	limit/base	current	history1	history2
Iron	ppm	ASTM D6130	>15	0	▲ 82	511
Aluminum	ppm	ASTM D6130	>10	0	<u>42</u>	1 56
Copper	ppm	ASTM D6130	>10	<1	0	<1
Lead	ppm	ASTM D6130	>10	<1	0	1
Tin	ppm	ASTM D6130	>10	<1	0	<1
Zinc	ppm	ASTM D6130		0	39	84
CONTAMINANTS		method	limit/base	current	history1	history2
Chlorine	ppm	ASTM D6130		8	2	80
CARRIER SALTS		method	limit/base	current	history1	history2
Sodium	ppm	ASTM D6130	1075	2903	815	555
Potassium	ppm	ASTM D6130	5	158	307	583
SCALE POTENTI	AL	method	limit/base	current	history1	history2
Calcium	ppm	ASTM D6130		4	0	2
Magnesium	ppm	ASTM D6130		<1	0	4
	PP.11			٠.	Ü	



COOLANT REPORT









Laboratory Sample No.

Lab Number **Unique Number**

: NX06027000 : 06027000 : 10776791

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Diagnosed Test Package : COOL- (Additional Tests: COOL, ICP)

: 06 Dec 2023 : 11 Dec 2023 Diagnostician : Doug Bogart

US 60606 Contact: DEVIN LINEHAN DLinehan@nordex-online.com

300 SOUTH WACKER DRIVE, SUITE 1500

T: (312)386-4124 F: (312)386-7102

NORDEX USA - Chicago

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CHICAGO, IL