

OIL ANALYSIS REPORT

Sample Rating Trend



Area SCHTRUCK Machine Id 6268 [SCHTRUCK] Component

Diesel Engine

PETRO CANADA DURON SHP 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


AL)			Mar2023	Nov2023		
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0006012	SBP0004166	
Sample Date		Client Info		29 Nov 2023	15 Mar 2023	
Machine Age	mls	Client Info		514932	479292	
Oil Age	mls	Client Info		35640	40069	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>6.0	<1.0	<1.0	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	36	31	
Chromium	ppm	ASTM D5185m	>20	1	2	
Nickel	ppm	ASTM D5185m	>2	1	<1	
Titanium	ppm	ASTM D5185m		0	<1	
Silver	ppm	ASTM D5185m	>2	0	<1	
Aluminum	ppm	ASTM D5185m	>25	25	10	
Lead	ppm	ASTM D5185m	>40	3	5	
Copper	ppm	ASTM D5185m	>330	2	2	
Tin	ppm	ASTM D5185m	>15	<1	2	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<1	15	
Barium	ppm	ASTM D5185m	0	0	0	
Molybdenum	ppm	ASTM D5185m	60	54	44	
Manganese	ppm	ASTM D5185m	0	<1	2	
Magnesium	ppm	ASTM D5185m	1010	951	626	
Calcium	ppm	ASTM D5185m	1070	1136	1715	
Phosphorus	ppm	ASTM D5185m	1150	957	704	
Zinc	ppm	ASTM D5185m	1270	1228	1013	
Sulfur	ppm	ASTM D5185m	2060	2221	2626	
						history2
CONTAMINANTS		method	limit/base	current	history1	mstoryz
	ppm		limit/base	current 8	history1 10	
Silicon	ppm ppm					
Silicon Sodium		ASTM D5185m		8	10	
Silicon Sodium	ppm	ASTM D5185m ASTM D5185m	>25	8 8	10 6	
Silicon Sodium Potassium INFRA-RED	ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>25 >20	8 8 66	10 6 4	
Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method	>25 >20 limit/base	8 8 66 current	10 6 4 history1	 history2
Silicon Sodium Potassium	ppm ppm %	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844	>25 >20 limit/base >3 >20	8 8 66 current 1	10 6 4 history1 0.7	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624	>25 >20 limit/base >3 >20	8 8 66 current 1 11.2	10 6 4 history1 0.7 12.9	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m •ASTM D7844 •ASTM D7844 •ASTM D7624	>25 >20 limit/base >3 >20 >30	8 8 66 current 1 11.2 25.5	10 6 4 history1 0.7 12.9 26.3	 history2




OIL ANALYSIS REPORT









To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

doty@liquidtrucking.com

T: (402)949-9398

Page 2 of 2

F: