

# **OIL ANALYSIS REPORT**

Sample Rating Trend





#### Component Hydraulic System Fluid AW HYDRAULIC OIL ISO 46 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

## Wear

All component wear rates are normal.

## Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


|                                   |                  | Oct2023              | 0ct2023            | Oct2023 Oct2023 | Nov2023          |                  |
|-----------------------------------|------------------|----------------------|--------------------|-----------------|------------------|------------------|
| SAMPLE INFORM                     | IATION           | method               | limit/base         | current         | history1         | history2         |
| Sample Number                     |                  | Client Info          |                    | KL0013161       | KL0012972        | KL0012733        |
| Sample Date                       |                  | Client Info          |                    | 30 Nov 2023     | 24 Oct 2023      | 18 Oct 2023      |
| Machine Age                       | hrs              | Client Info          |                    | 0               | 0                | 0                |
| Oil Age                           | hrs              | Client Info          |                    | 0               | 0                | 0                |
| Oil Changed                       |                  | Client Info          |                    | N/A             | N/A              | N/A              |
| Sample Status                     |                  |                      |                    | NORMAL          | NORMAL           | NORMAL           |
| CONTAMINATION                     | ٧                | method               | limit/base         | current         | history1         | history2         |
| Water                             |                  | WC Method            | >0.1               | NEG             | NEG              | NEG              |
| WEAR METALS                       |                  | method               | limit/base         | current         | history1         | history2         |
| Iron                              | ppm              | ASTM D5185m          | >20                | <1              | 0                | 0                |
| Chromium                          | ppm              | ASTM D5185m          | >10                | <1              | 0                | 0                |
| Nickel                            | ppm              | ASTM D5185m          | >10                | 0               | 0                | 0                |
| Titanium                          | ppm              | ASTM D5185m          |                    | 0               | 0                | 0                |
| Silver                            | ppm              | ASTM D5185m          |                    | 0               | 0                | 0                |
| Aluminum                          | ppm              | ASTM D5185m          | >10                | <1              | 0                | 0                |
| Lead                              | ppm              | ASTM D5185m          | >10                | 0               | 0                | 0                |
| Copper                            | ppm              | ASTM D5185m          | >75                | <1              | 0                | 1                |
| Tin                               | ppm              | ASTM D5185m          | >10                | 0               | 0                | 0                |
| Vanadium                          | ppm              | ASTM D5185m          |                    | 0               | 0                | 0                |
| Cadmium                           | ppm              | ASTM D5185m          |                    | 0               | 0                | 0                |
| ADDITIVES                         |                  | method               | limit/base         | current         | history1         | history2         |
| Boron                             | ppm              | ASTM D5185m          | 5                  | 0               | 0                | 0                |
| Barium                            | ppm              | ASTM D5185m          | 5                  | 0               | 0                | 0                |
| Molybdenum                        | ppm              | ASTM D5185m          | 5                  | <1              | 0                | 0                |
| Manganese                         | ppm              | ASTM D5185m          |                    | 0               | 0                | 0                |
| Magnesium                         | ppm              | ASTM D5185m          | 25                 | 2               | 0                | <1               |
| Calcium                           | ppm              | ASTM D5185m          | 200                | 50              | 44               | 52               |
| Phosphorus                        | ppm              | ASTM D5185m          | 300                | 314             | 297              | 325              |
| Zinc                              | ppm              | ASTM D5185m          | 370                | 404             | 374              | 417              |
| Sulfur                            | ppm              | ASTM D5185m          | 2500               | 2468            | 1955             | 2361             |
| CONTAMINANTS                      |                  | method               | limit/base         | current         | history1         | history2         |
| Silicon                           | ppm              | ASTM D5185m          | >20                | 2               | 1                | 2                |
| Sodium                            | ppm              | ASTM D5185m          |                    | 0               | 0                | <1               |
| Potassium                         | ppm              | ASTM D5185m          | >20                | <1              | 0                | 0                |
| FLUID CLEANLIN                    | ESS              | method               | limit/base         | current         | history1         | history2         |
| Particles >4µm                    |                  | ASTM D7647           | >5000              | 1369            | 2624             | 2376             |
| Particles >6µm                    |                  | ASTM D7647           | >1300              | 255             | 524              | 367              |
| Particles >14µm                   |                  | ASTM D7647           | >160               | 18              | 32               | 18               |
| Particles >21µm                   |                  | ASTM D7647           | >40                | 4               | 8                | 4                |
| Particles >38µm                   |                  | ASTM D7647           | >10                | 1               | 1                | 1                |
| Particles >71µm                   |                  | ASTM D7647           | >3                 | 0               | 0                | 0                |
| Oil Cleanliness                   |                  | ISO 4406 (c)         | >19/17/14          | 18/15/11        | 19/16/12         | 18/16/11         |
|                                   |                  |                      |                    |                 |                  |                  |
| FLUID DEGRADA                     | TION             | method               | limit/base         | current         | history1         | history2         |
| FLUID DEGRADA<br>Acid Number (AN) | TION<br>mg KOH/g | method<br>ASTM D8045 | limit/base<br>0.57 | current<br>0.31 | history1<br>0.37 | history2<br>0.32 |


Report Id: PATMIDTX [WUSCAR] 06027684 (Generated: 12/08/2023 12:52:32) Rev: 1


Page 1 of 2



# **OIL ANALYSIS REPORT**








| VISUAL           |        | method    | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal     | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Precipitate      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Silt             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Debris           | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Sand/Dirt        | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Appearance       | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Odor             | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Emulsified Water | scalar | *Visual   | >0.1       | NEG     | NEG      | NEG      |
| Free Water       | scalar | *Visual   |            | NEG     | NEG      | NEG      |
| FLUID PROPERTIES |        | method    | limit/base | current | history1 | history2 |
| Visc @ 40°C      | cSt    | ASTM D445 | 46         | 48.6    | 48.3     | 50.2     |
| SAMPLE IMAGES    |        | method    | limit/base | current | history1 | history2 |
| Color            |        |           |            |         |          |          |
| <b>D</b>         |        |           |            |         |          |          |

Bottom



Contact/Location: RICKY MATA - PATMIDTX