




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
FINISHING
Machine Id
1210HP01

Component
Hydraulic System
Fluid

KLUBER SUMMIT HYSYN FG 46 (40 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	WC0842379	WC0761386	WC0668065
Sample Date	Client Info	28 Nov 2023	23 May 2023	30 Nov 2022
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	Not Chngd	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184	20	15	9
Iron	ppm	ASTM D5185m >20	11	10
Chromium	ppm	ASTM D5185m >20	2	2
Nickel	ppm	ASTM D5185m >20	0	0
Titanium	ppm	ASTM D5185m	<1	<1
Silver	ppm	ASTM D5185m	0	0
Aluminum	ppm	ASTM D5185m >20	2	0
Lead	ppm	ASTM D5185m >20	0	0
Copper	ppm	ASTM D5185m >20	<1	<1
Tin	ppm	ASTM D5185m >20	0	<1
Vanadium	ppm	ASTM D5185m	0	<1
Cadmium	ppm	ASTM D5185m	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0
Barium	ppm	ASTM D5185m	5	0
Molybdenum	ppm	ASTM D5185m	1	0
Manganese	ppm	ASTM D5185m	0	<1
Magnesium	ppm	ASTM D5185m	<1	2
Calcium	ppm	ASTM D5185m	121	130
Phosphorus	ppm	ASTM D5185m	447	437
Zinc	ppm	ASTM D5185m	470	471
Sulfur	ppm	ASTM D5185m	6866	7258

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	2	2
Sodium	ppm	ASTM D5185m	<1	3
Potassium	ppm	ASTM D5185m >20	2	0
Water	%	ASTM D6304 >0.05	0.002	0.011
ppm Water	ppm	ASTM D6304 >500	21	115.0

FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >10000	1200	474	1057
Particles >6µm	ASTM D7647 >2500	417	68	201
Particles >14µm	ASTM D7647 >320	87	14	26
Particles >21µm	ASTM D7647 >80	39	5	7
Particles >38µm	ASTM D7647 >20	2	1	2
Particles >71µm	ASTM D7647 >4	0	0	0
Oil Cleanliness	ISO 4406 (c) >20/18/15	17/16/14	16/13/11	17/15/12

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.42	0.46




OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 46	42.9	43.4	43.4

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0842379
Lab Number : 06027721
Unique Number : 10777512
Test Package : IND 2 (Additional Tests: KF, PQ)

ARAUCO FLAKEBOARD - MDF
 985 CORINTH RD
 MONCURE, NC
 US
 Contact: CHRISTOPHER JACKSON
 christopher.jackson@arauco.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)