

OIL ANALYSIS REPORT

Area AIRLUBE 228 ATLAS COPCO API628-168 - GESTAMP 7 Component

Compressor

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06029483		
Sample Date		Client Info		28 Nov 2023		
Machine Age	hrs	Client Info		31850		
Oil Age	hrs	Client Info		6182		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>5	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	13		
Lead	ppm	ASTM D5185m	>65	0		
Copper	ppm	ASTM D5185m	>65	<1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	1.5	0		
Barium	ppm	ASTM D5185m	0	0		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m	0.3	<1		
Magnesium	ppm	ASTM D5185m	0	0		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	406	110		
Zinc	ppm	ASTM D5185m	0	0		
Sulfur	ppm	ASTM D5185m	1283	0		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	0		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.463	0.90		



44 Abnormal 42. 40 Nov28/23

OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Nov28/23	Appearance	scalar	*Visual	NORML	NORML		
N	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	47.9	54.0		
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Nov28/23 -	Color				a.	no image	no image
	Bottom					no image	no image
	GRAPHS Ferrous Alloys	ıls		Nov28/23			
	Viscosity @ 40°C			Nov28/23	Acid Number		
	Abnorma C 50 Base 45 Abnormal 40 E			23 Acid Number (mg KOH/g)	J.U		33
l et en tem	Nov28/23		A C	Nov28/23	Nov28/23		01010100100150
Laboratory Sample No. Lab Number Unique Number Test Package to discuss this sample report,	: IND 2 contact Customer Serv	Recieved Diagnose Diagnose	d : 08 ed : 19 tician : Jon 800-237-1369	Dec 2023 Dec 2023 athan Heste 9.	er	400 MIDI Contact:	CHNOLOGIES WRIGHT AVE DLETOWN, OH US 45044 APRIL MOORE mpressors.com
- Denotes test methods that a Statements of conformity to spec					(JCGM 106:2012)	F:	T: (513)539-6040

Contact/Location: APRIL MOORE - UCDIRMID