



OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL




Area
AZURE SKY [200007684]

Machine Id
T-37

Component
Wind Turbine Gearbox

Fluid
FUCHS RENOLIN UNISYN CLP 320 (580 LTR)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	NX06054786	NX06054821	---
Sample Date	Client Info	07 Jan 2024	04 Mar 2023	---
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	Not Changed	Not Changed	---
Sample Status		NORMAL	ABNORMAL	---

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184	>50	14	10
Iron	ppm	ASTM D5185m	>30	6
Chromium	ppm	ASTM D5185m	>3	0
Nickel	ppm	ASTM D5185m	>3	0
Titanium	ppm	ASTM D5185m	>10	0
Silver	ppm	ASTM D5185m		0
Aluminum	ppm	ASTM D5185m	>30	0
Lead	ppm	ASTM D5185m	>15	0
Copper	ppm	ASTM D5185m	>10	0
Tin	ppm	ASTM D5185m	>10	0
Vanadium	ppm	ASTM D5185m		0
Cadmium	ppm	ASTM D5185m		0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		5
Barium	ppm	ASTM D5185m		0
Molybdenum	ppm	ASTM D5185m		0
Manganese	ppm	ASTM D5185m		0
Magnesium	ppm	ASTM D5185m		0
Calcium	ppm	ASTM D5185m		9
Phosphorus	ppm	ASTM D5185m		191
Zinc	ppm	ASTM D5185m		0
Sulfur	ppm	ASTM D5185m		4621

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+15	0
Sodium	ppm	ASTM D5185m		5
Potassium	ppm	ASTM D5185m	>20	0
Water	%	ASTM D6304	>0.02	0.003
ppm Water	ppm	ASTM D6304	>200	35

FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		501	2516
Particles >6µm	ASTM D7647	>320	252	▲ 747
Particles >14µm	ASTM D7647	>40	30	▲ 58
Particles >21µm	ASTM D7647	>10	4	10
Particles >38µm	ASTM D7647	>3	0	0
Particles >71µm	ASTM D7647	>3	0	0
Oil Cleanliness	ISO 4406 (c)	>--/15/12	16/15/12	▲ 19/17/13

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.6	0.33




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.02	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	321	319

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : NX06054786 **Received** : 08 Jan 2024
Lab Number : 06054786 **Diagnosed** : 10 Jan 2024
Unique Number : 10820735 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PQ, PrtCount)

NORDEX USA - Chicago
 300 SOUTH WACKER DRIVE, SUITE 1500
 CHICAGO, IL
 US 60606
 Contact: DEVIN LINEHAN
 DLinehan@nordex-online.com
 T: (312)386-4124
 F: (312)386-7102

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)