




OIL ANALYSIS REPORT

Sample Rating Trend

ISO



Area
MARYNEAL [200006807]
 Machine Id
87027 SITE 32
 Component
Wind Turbine Gearbox
 Fluid
FUCHS RENOLIN CLP ISO 320 (650 LTR)



DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		NX06054859	NX009234	---
Sample Date	Client Info		20 Oct 2023	31 Jan 2022	---
Machine Age	hrs	Client Info	0	0	---
Oil Age	hrs	Client Info	0	0	---
Oil Changed	Client Info		N/A	N/A	---
Sample Status			ATTENTION	NORMAL	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184	>80	12	17	---
Iron	ppm	ASTM D5185m	>150	13	11
Chromium	ppm	ASTM D5185m	>5	0	<1
Nickel	ppm	ASTM D5185m	>10	0	0
Titanium	ppm	ASTM D5185m	>10	0	0
Silver	ppm	ASTM D5185m		0	<1
Aluminum	ppm	ASTM D5185m	>10	0	11
Lead	ppm	ASTM D5185m	>20	<1	2
Copper	ppm	ASTM D5185m	>50	<1	<1
Tin	ppm	ASTM D5185m	>3	0	<1
Antimony	ppm	ASTM D5185m	>3	---	0
Vanadium	ppm	ASTM D5185m		0	0
Cadmium	ppm	ASTM D5185m		0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		6	8
Barium	ppm	ASTM D5185m		0	0
Molybdenum	ppm	ASTM D5185m		0	0
Manganese	ppm	ASTM D5185m		0	<1
Magnesium	ppm	ASTM D5185m		0	0
Calcium	ppm	ASTM D5185m		10	19
Phosphorus	ppm	ASTM D5185m		183	201
Zinc	ppm	ASTM D5185m		0	0
Sulfur	ppm	ASTM D5185m		4645	4063

CONTAMINANTS






	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	12	25
Sodium	ppm	ASTM D5185m	>20	5	0
Potassium	ppm	ASTM D5185m	>20	0	<1
Water	%	ASTM D6304	>0.05	0.003	0.002
ppm Water	ppm	ASTM D6304	>500	28	24.1

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		19154	21317	---
Particles >6µm	ASTM D7647	>2500	▲ 4319	381	---
Particles >14µm	ASTM D7647	>320	168	25	---
Particles >21µm	ASTM D7647	>80	23	9	---
Particles >38µm	ASTM D7647	>20	0	0	---
Particles >71µm	ASTM D7647	>4	0	0	---
Oil Cleanliness	ISO 4406 (c)	>--/18/15	▲ 21/19/15	22/16/12	---



OIL ANALYSIS REPORT




FLUID DEGRADATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.39	0.36	---





VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.05	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	328	319	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : NX06054859 **Received** : 08 Jan 2024
Lab Number : 06054859 **Diagnosed** : 10 Jan 2024
Unique Number : 10820808 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PQ, PrtCount)

NORDEX USA - Chicago
 300 SOUTH WACKER DRIVE, SUITE 1500
 CHICAGO, IL
 US 60606
 Contact: DEVIN LINEHAN
 DLinehan@nordex-online.com
 T: (312)386-4124
 F: (312)386-7102

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)