




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
MARYNEAL [200006807]
 Machine Id
87054 SITE 6
 Component
Wind Turbine Gearbox
 Fluid
FUCHS RENOLIN CLP ISO 320 (650 LTR)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		NX06054884	NX009376	---
Sample Date	Client Info		14 Nov 2023	11 Jan 2022	---
Machine Age	hrs	Client Info	0	0	---
Oil Age	hrs	Client Info	0	0	---
Oil Changed	Client Info		N/A	N/A	---
Sample Status			NORMAL	NORMAL	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184	>80	16	15	---
Iron	ppm	ASTM D5185m	>150	8	13
Chromium	ppm	ASTM D5185m	>5	0	<1
Nickel	ppm	ASTM D5185m	>10	0	0
Titanium	ppm	ASTM D5185m	>10	0	0
Silver	ppm	ASTM D5185m		0	<1
Aluminum	ppm	ASTM D5185m	>10	0	<1
Lead	ppm	ASTM D5185m	>20	0	<1
Copper	ppm	ASTM D5185m	>50	0	<1
Tin	ppm	ASTM D5185m	>3	0	<1
Antimony	ppm	ASTM D5185m	>3	---	0
Vanadium	ppm	ASTM D5185m		0	0
Cadmium	ppm	ASTM D5185m		0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2	6
Barium	ppm	ASTM D5185m		0	0
Molybdenum	ppm	ASTM D5185m		0	0
Manganese	ppm	ASTM D5185m		0	<1
Magnesium	ppm	ASTM D5185m		0	0
Calcium	ppm	ASTM D5185m		8	18
Phosphorus	ppm	ASTM D5185m		163	192
Zinc	ppm	ASTM D5185m		0	0
Sulfur	ppm	ASTM D5185m		4144	3791

CONTAMINANTS






	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	7	24
Sodium	ppm	ASTM D5185m	>20	5	0
Potassium	ppm	ASTM D5185m	>20	0	<1
Water	%	ASTM D6304	>0.05	0.003	0.001
ppm Water	ppm	ASTM D6304	>500	26	11.8

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		4156	22111	---
Particles >6µm	ASTM D7647	>2500	1122	278	---
Particles >14µm	ASTM D7647	>320	97	19	---
Particles >21µm	ASTM D7647	>80	26	7	---
Particles >38µm	ASTM D7647	>20	1	0	---
Particles >71µm	ASTM D7647	>4	0	0	---
Oil Cleanliness	ISO 4406 (c)	>--/18/15	19/17/14	22/15/11	---



OIL ANALYSIS REPORT




FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.34	0.36	---



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	LIGHT	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	---
Free Water	scalar	*Visual		NEG	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	320	323	327	---

SAMPLE IMAGES



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : NX06054884 **Received** : 08 Jan 2024
Lab Number : 06054884 **Diagnosed** : 10 Jan 2024
Unique Number : 10820833 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PQ, PrtCount)

NORDEX USA - Chicago
 300 SOUTH WACKER DRIVE, SUITE 1500
 CHICAGO, IL
 US 60606
 Contact: DEVIN LINEHAN
 DLinehan@nordex-online.com
 T: (312)386-4124
 F: (312)386-7102

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)