




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**SSC**  
 Machine Id  
**NIRO 4 (S/N 006)**  
 Component  
**Transmission (Manual)**  
 Fluid  
**DTE 10-150 (15 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>USP0005227</b>	USP239565	USP246493
Sample Date	Client Info	<b>03 Jan 2024</b>	05 Dec 2023	10 Nov 2023
Machine Age	mths Client Info	<b>1728</b>	0	0
Oil Age	mths Client Info	<b>0</b>	0	0
Oil Changed	Client Info	<b>N/A</b>	N/A	N/A
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >200	<b>7</b>	4	3
Chromium	ppm ASTM D5185m >5	<b>&lt;1</b>	0	0
Nickel	ppm ASTM D5185m >5	<b>&lt;1</b>	<1	0
Titanium	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Silver	ppm ASTM D5185m >7	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >25	<b>0</b>	0	0
Lead	ppm ASTM D5185m >45	<b>4</b>	2	3
Copper	ppm ASTM D5185m >225	<b>2</b>	1	1
Tin	ppm ASTM D5185m >10	<b>2</b>	2	1
Vanadium	ppm ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm ASTM D5185m	<b>&lt;1</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	<b>0</b>	0	0
Barium	ppm ASTM D5185m	<b>0</b>	<1	0
Molybdenum	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Manganese	ppm ASTM D5185m	<b>&lt;1</b>	<1	0
Magnesium	ppm ASTM D5185m	<b>3</b>	2	0
Calcium	ppm ASTM D5185m	<b>50</b>	61	65
Phosphorus	ppm ASTM D5185m	<b>143</b>	143	125
Zinc	ppm ASTM D5185m	<b>0</b>	0	2
Sulfur	ppm ASTM D5185m	<b>1039</b>	1039	925

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >125	<b>2</b>	1	<1
Sodium	ppm ASTM D5185m	<b>0</b>	<1	<1
Potassium	ppm ASTM D5185m >20	<b>1</b>	<1	0
Water	% ASTM D6304 >0.1	<b>0.002</b>	0.003	0.005
ppm Water	ppm ASTM D6304 >1000	<b>24</b>	32	59.8

## FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >10000	<b>1019</b>	1224	1288
Particles >6µm	ASTM D7647 >2500	<b>290</b>	302	386
Particles >14µm	ASTM D7647 >320	<b>18</b>	24	24
Particles >21µm	ASTM D7647 >80	<b>6</b>	6	5
Particles >38µm	ASTM D7647 >20	<b>0</b>	0	0
Particles >71µm	ASTM D7647 >4	<b>0</b>	0	0
Oil Cleanliness	ISO 4406 (c) >20/18/15	<b>17/15/11</b>	17/15/12	17/16/12

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g ASTM D8045	<b>0.18</b>	0.09	0.09




# OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	153	152	151

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : USP0005227 **Received** : 08 Jan 2024  
**Lab Number** : 06054948 **Diagnosed** : 10 Jan 2024  
**Unique Number** : 10820897 **Diagnostician** : Doug Bogart  
**Test Package** : IND 2

**EMPIRICAL FOODS INC. - BPIISOUPRO - EMPSOUPRO**  
 S. SIOUX CITY, NE  
 US  
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: