


OIL ANALYSIS REPORT



Area [CONHER] CATERPILLAR Pisa 4 Aux-1 - Pacifico Industrial Component **Diesel Engine**

CHEVRON DELO 400 MULTIGRADE 15W40 (30 LTR)



| DIAGNOSIS | SAMPLE INFORM | ATION | method | limit/base | current | history1 | history2 |
|--|---------------|-------|-------------|------------|-------------|----------|-----------|
| Recommendation | Sample Number | | Client Info | | KL0013447 | | |
| Oil and filter change at the time of sampling has | Sample Date | | Client Info | | 13 Dec 2023 | | |
| been noted. No corrective action is recommended | Machine Age | hrs | Client Info | | 0 | | |
| at this time. Resample at the next service interval to | Oil Age | hrs | Client Info | | 0 | | |
| monitor. | Oil Changed | | Client Info | | Changed | | |
| Wear | Sample Status | | | | ABNORMAL | | |
| All component wear rates are normal. | CONTAMINATION | | method | limit/base | ourropt | history1 | history2 |
| Contamination | | | | | current | historyi | TIIStOLY2 |
| There is a high amount of particulates present in the oil. | Fuel | | | >5 | <1.0 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| Fluid Condition | Glycol | | WC Method | | NEG | | |
| The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the | WEAR METALS | | method | limit/base | current | history1 | history2 |
| oil is suitable for further service. | Iron | ppm | ASTM D5185m | >105 | 13 | | |
| | | ppm | ASTM D5185m | >5 | <1 | | |
| | Nickel | ppm | ASTM D5185m | >4 | 0 | | |
| | Titanium | ppm | ASTM D5185m | >2 | 0 | | |
| | Silver | ppm | ASTM D5185m | >2 | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >10 | 1 | | |
| | Lead | ppm | ASTM D5185m | >15 | 0 | | |
| | Copper | ppm | ASTM D5185m | >140 | 1 | | |
| | Tin | ppm | ASTM D5185m | >4 | 0 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | Cadmium | ppm | ASTM D5185m | | 0 | | |
| | ADDITIVES | | method | limit/base | current | history1 | history2 |
| | Boron | ppm | ASTM D5185m | 151 | 3 | | |
| | | ppm | ASTM D5185m | | 0 | | |
| | Molybdenum | ppm | ASTM D5185m | 250 | 19 | | |
| | Manganese | ppm | ASTM D5185m | | 0 | | |
| | Magnesium | ppm | ASTM D5185m | 0 | 930 | | |
| | Calcium | ppm | ASTM D5185m | 2046 | 1602 | | |
| | Phosphorus | ppm | ASTM D5185m | 1043 | 952 | | |
| | Zinc | ppm | ASTM D5185m | 943 | 1121 | | |
| | Sulfur | ppm | ASTM D5185m | 5012 | 3477 | | |
| | CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| | Silicon | ppm | ASTM D5185m | >25 | 14 | | |
| | | ppm | ASTM D5185m | | 5 | | |
| | | ppm | ASTM D5185m | >20 | 2 | | |
| | INFRA-RED | | method | limit/base | current | history1 | history2 |

| INFRA-RED | | method | limit/base | current | history1 | history2 |
|-----------|----------|-------------|------------|---------|----------|----------|
| Soot % | % | *ASTM D7844 | >3 | 0.1 | | |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 3.9 | | |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 13.6 | | |


Report Id: CONHERKL [WUSCAR] 06055991 (Generated: 01/11/2024 11:41:27) Rev: 1




OIL ANALYSIS REPORT









| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
|-------------------|----------|--------------|--|---------------------------------|----------|--|
| Particles >4µm | | ASTM D7647 | | 50241 | | |
| Particles >6µm | | ASTM D7647 | >5000 | <u> </u> | | |
| Particles >14µm | | ASTM D7647 | >640 | 4658 | | |
| Particles >21µm | | ASTM D7647 | >160 | <u> </u> | | |
| Particles >38µm | | ASTM D7647 | >40 | A 242 | | |
| Particles >71µm | | ASTM D7647 | >10 | <u> </u> | | |
| Oil Cleanliness | | ISO 4406 (c) | >19/16 | A 22/19 | | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 7.2 | | |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 12.5 | 10.16 | | |
| VISUAL | | method | limit/base | current | history1 | history2 |
| White Metal | scalar | *Visual | NONE | NONE | | |
| Yellow Metal | scalar | *Visual | NONE | NONE | | |
| Precipitate | scalar | *Visual | NONE | NONE | | |
| Silt | scalar | *Visual | NONE | NONE | | |
| Debris | scalar | *Visual | NONE | NONE | | |
| Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| Appearance | scalar | *Visual | NORML | NORML | | |
| Odor | scalar | *Visual | NORML | NORML | | |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| Free Water | scalar | *Visual | | NEG | | |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 14.3 | | |
| GRAPHS | | | | | | |
| Ferrous Alloys | | | 491,52 | Particle Count | t | TŽ |
| iron | | | 122,88 | | | |
| 10 - nickel | | | | | | -2 |
| 5- | | | 30,72 | | | ti i |
| 23 | ****** | | EZ/ (E 7.68 | 0- | | |
| Dec13/23 | | | Dec13/23 16r 1 ml | 0- | | |
| Non-ferrous Metal | s | | of particles (per 1 ml) 89 2.2 | 0- | | |
| Copper 1 | | | d jo 12 | 0- | | |
| management lead | | | Jaquinu 3 | | | |
| 5- tin | | | | | | |
| | ***** | ***** | | ⁸ Sibreve mal | | +1 |
| Dec13/23 | | | Dec13/23 | 2 - | | - |
| | | | Dei | 0. 4µ 6µ | 14µ 21µ | 38µ 71µ |
| Viscosity @ 100°C | | | (B., | Base Number | | to a second and the second |
| Abnormal | | | H 15. | Base | | |
| | | | ະ 10. | 0 - | | |
| 4 Base | | | EL . | | | |
| Abnormal | | | (0/H0) Base Number 10. 10. 10. | 0- | | |

Dec13/23 -

: 09 Jan 2024

: 11 Jan 2024

Diagnostician : Don Baldridge

Dec13/23



: WearCheck USA - 501 Madison Ave., Cary, NC 27513 CONOR JUAREZ 348 HERMOSILLO, MX 83140 Contact: EDUARDO GARCIA egarcia.comsa@gmail.com T: (526)622-1581 x:81 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: x:

Certificate L2367

Dec13/23

: KL0013447

Test Package : MOB 2 (Additional Tests: PrtCount)

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: 06055991

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Recieved

Diagnosed

Laboratory

Sample No.

Lab Number

Unique Number : 10821940

Dec13/23