

# **OIL ANALYSIS REPORT**

Sample Rating Trend

ISO

# Machine Id KAESER AS 30T 286445 (S/N 1064)

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

#### ▲ Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

### Contamination

There is a moderate amount of particulates present in the oil.

#### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| 3/N 1064)     |          |             |            |             |          | <b>Y</b> / <b>A</b> |
|---------------|----------|-------------|------------|-------------|----------|---------------------|
|               |          |             |            |             |          |                     |
|               |          |             |            |             |          |                     |
|               |          |             |            | Dec2023     |          |                     |
| SAMPLE INFORM | MATION   | method      | limit/base | current     | history1 | history2            |
| Sample Number |          | Client Info |            | KCPA007702  |          |                     |
| Sample Date   |          | Client Info |            | 27 Dec 2023 |          |                     |
| Machine Age   | hrs      | Client Info |            | 7156        |          |                     |
| Oil Age       | hrs      | Client Info |            | 0           |          |                     |
| Oil Changed   |          | Client Info |            | N/A         |          |                     |
| Sample Status |          |             |            | ATTENTION   |          |                     |
| WEAR METALS   |          | method      | limit/base | current     | history1 | history2            |
| Iron          | ppm      | ASTM D5185m | >50        | 7           |          |                     |
| Chromium      | ppm      | ASTM D5185m | >10        | 0           |          |                     |
| Nickel        | ppm      | ASTM D5185m | >3         | 0           |          |                     |
| Titanium      | ppm      | ASTM D5185m | >3         | 0           |          |                     |
| Silver        | ppm      | ASTM D5185m | >2         | 0           |          |                     |
| Aluminum      | ppm      | ASTM D5185m | >10        | 2           |          |                     |
| Lead          | ppm      | ASTM D5185m | >10        | 0           |          |                     |
| Copper        | ppm      | ASTM D5185m | >50        | 7           |          |                     |
| Tin           | ppm      | ASTM D5185m | >10        | <1          |          |                     |
| Vanadium      | ppm      | ASTM D5185m |            | 0           |          |                     |
| Cadmium       | ppm      | ASTM D5185m |            | 0           |          |                     |
| ADDITIVES     |          | method      | limit/base | current     | history1 | history2            |
| Boron         | ppm      | ASTM D5185m |            | 0           |          |                     |
| Barium        | ppm      | ASTM D5185m | 90         | 0           |          |                     |
| Molybdenum    | ppm      | ASTM D5185m |            | 0           |          |                     |
| Manganese     | ppm      | ASTM D5185m |            | <1          |          |                     |
| Magnesium     | ppm      | ASTM D5185m | 90         | 0           |          |                     |
| Calcium       | ppm      | ASTM D5185m | 2          | 0           |          |                     |
| Phosphorus    | ppm      | ASTM D5185m |            | 470         |          |                     |
| Zinc          | ppm      | ASTM D5185m |            | 383         |          |                     |
| Sulfur        | ppm      | ASTM D5185m |            | 2152        |          |                     |
| CONTAMINANTS  | <u> </u> | method      | limit/base | current     | history1 | history2            |

| Manganese  | ppm   | ASTM D5185m  |  | <1                               |          |          |
|--|-------|--|--|----------------------------------|----------|----------|
| Magnesium  | ppm   | ASTM D5185m  | 90                                       | 0                                |          |          |
| Calcium  | ppm   | ASTM D5185m  | 2  | 0                                |          |          |
| Phosphorus   | ppm   | ASTM D5185m  |  | 470                              |          |          |
| Zinc   | ppm   | ASTM D5185m  |  | 383                              |          |          |
| Sulfur   | ppm   | ASTM D5185m  |  | 2152                             |          |          |
| CONTAMINANTS   | 3     | method   | limit/base                               | current                          | history1 | history2 |
| Silicon  | ppm   | ASTM D5185m  | >25                                      | <1                               |          |          |
| Sodium   | ppm   | ASTM D5185m  |  | <1                               |          |          |
| Potassium  | ppm   | ASTM D5185m  | >20                                      | <1                               |          |          |
| Water  | %     | ASTM D6304   | >0.05                                    | 0.005                            |          |          |
| ppm Water  | ppm   | ASTM D6304   | >500                                     | 58                               |          |          |
| ppiii watei  | ppiii | AOTIVI DOJUH   | >500                                     | 30                               |          |          |
| FLUID CLEANLIN   |       | method   | limit/base                               | current                          | history1 | history2 |
| • •  |       |  |  |                                  |          | history2 |
| FLUID CLEANLIN   |       | method   |  | current                          |          | ,        |
| FLUID CLEANLIN Particles >4μm  |       | method<br>ASTM D7647   | limit/base                               | current<br>8320                  | history1 |          |
| FLUID CLEANLIN Particles >4μm Particles >6μm   |       | method ASTM D7647 ASTM D7647   | limit/base >1300                         | current<br>8320<br><b>△</b> 2056 | history1 |          |
| FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm                 |       | method  ASTM D7647  ASTM D7647  ASTM D7647                               | limit/base >1300 >80                     | current 8320  2056  125          | history1 |          |
| FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm                                 |       | method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647                       | >1300<br>>80<br>>20                      | current  8320  2056  125  26     | history1 |          |
| FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm                 |       | method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647            | limit/base >1300 >80 >20 >4              | current  8320  2056  125  26  0  | history1 |          |
| FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm | IESS  | method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 | limit/base   >1300   >80   >20   >4   >3 | current  8320  2056  125  26  0  | history1 |          |



## **OIL ANALYSIS REPORT**



To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

renny.kroge@kaeser.com;

T: (303)371-2500 F: (888)368-0838