

OIL ANALYSIS REPORT

DANIS IND. CORP. BLDG. LINK-BELT RTC-8065S II J9L1-6881 Component

Front Right Planetary

GEAR OIL SAE 85W140 (--- GAL)





NORMAL

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Ť

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		LBC0000193		
Sample Date		Client Info		05 Jan 2024		
Machine Age	hrs	Client Info		1888		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
		ام م مالح میں			Istatawał	Isistem (O
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	17		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>75	1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	338		
Barium	ppm	ASTM D5185m	200	0		
Molybdenum	ppm	ASTM D5185m	12	0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	12	0		
Calcium	ppm	ASTM D5185m	150	9		
Phosphorus	ppm	ASTM D5185m	1650	1062		
Zinc	ppm	ASTM D5185m	125	0		
Sulfur	ppm	ASTM D5185m	22500	23632		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon		ASTM D5185m	>75	1		
Sodium	ppm	ASTM D5185m	×10	۱ <1		
	ppm		> 20	3		
Potassium	ppm	ASTM D5185m		•		
VISUAL		method	limit/base		history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	LIGHT		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
3:36:06) Rev: 1					Submitted I	Bv: Tanner Wel



OIL ANALYSIS REPORT



Visc @ 40°C cSt ASTM D445 368 242		FLUID PROPERTIES		method limit/base		current	history1	history2
Color no image no image no image Bottom no image no image no image GRAPHS Ferrous Alloys for dramin for drami		Visc @ 40°C	cSt	ASTM D445	368	242		
Bottom no image no image no image CRAPHS Ferrous Alloys 0 0 0 0 0 0 0 0 0 0 0 0 0		SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
Bottom no image no image no image		Color				no image	no image	no image
Ferrous Alloys	Jan5,	Bottom				no image	no image	no image
Non-ferrous Metals		GRAPHS						
	ver	Non-ferrous Met						
		450 - Abnormal	2					
		T						
450 Abnomal 400 Base 300 C 300		Abnormal 200						
450 400 Base 350 250 250					lan5/24			
450 Abnomal 400 Base 300 300		Abnormal			Jan5/24			
Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Lab Number : U8arCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Lab Number : 106057029 Unique Number : 10822978 Diagnosed : 11 Jan 2024 Diagnostician : Wes Davis US 432	Sample No. Lab Number Unique Number	: LBC0000193 : 06057029 : 10822978	Recieved Diagnose	l :10. ed :11.	Jan 2024 Jan 2024	3 Colum	2329 Pei	rformance W Columbus, (US 432

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: