

## **OIL ANALYSIS REPORT**

Area SAINT ANSGAR Machine Id AT2402 LIQ #2 AGITATOR Component

**Agitator Gearbox** 

MOBIL COMPRESSOR OIL 220 (--- GAL)

## DIAGNOSIS

## Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.






NORMAL

SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0886341		
Sample Date		Client Info		03 Jan 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
PQ		ASTM D8184		12		
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		1		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		503		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		2150		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	22		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	<1		
Water	%	ASTM D6304	>0.1	NEG		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.87		



# **OIL ANALYSIS REPORT**





	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
4.015 net	Appearance	scalar	*Visual	NORML	NORML		
-	Oddr	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
1	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	220	225		
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
- P.C. Freel	Color					no image	no image
	Bottom				$(\bigcirc)$	no image	no image
	GRAPHS Ferrous Alloys						
	2 مالی کردیس Non-ferrous Meta	ls		Jan3/24			
	to the second se			Jan 3/24			
	Viscosity @ 40°C				Acid Number		
	240 - 6 230 - 6 220 - 6 220 - 7 200 - 7 20				8 6 4 2 0		
	Jan3/24			Jan3/24 .	Jan3/24		Jan3/24 •
Certificate 12367 Test Package To discuss this sample report	Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0886341 Recieved : 10 Jan 2024 Lab Number : 06057429 Diagnosed : 15 Jan 2024 Unique Number : 10823378 Diagnostician : Jonathan Hester						
* - Denotes test methods that Statements of conformity to spe					(JCGM 106:2012)		Т: F:

ñ

Ē

Submitted By: KYLE HUTCHINSON

Page 2 of 2