



GREASE ANALYSIS

Sample Rating Trend



VISUAL METAL



Machine Id
MAYSVILLE HOIST
 Component
Grease
 Fluid
MOBIL Mobilux EP 0 (--- GAL)

DIAGNOSIS

▲ Recommendation

There is some discrepancy possible with this sample regarding if it is a baseline reference or if there is a high speed and low speed coupling sample submitted. If this is a baseline sample, no other work needs to be done. If this is an active sample, some of the results for this and the subsequent grease sample are incorrect as they rely on a baseline reference sample submission from the customer. Analytical Ferrography: A minimal amount of wear is common in new grease samples, the noted moderate amount of white metal in the visuals review and the wear debris noted in the microscopic analysis are inconsequential to the component and should be considered normal. All other parameters are within specifications.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0896570	---	---
Sample Date	Client Info		08 Jan 2024	---	---
Machine Age	mths	Client Info	6	---	---
Grease Age	mths	Client Info	6	---	---
Grease Serviced	Client Info		Changed	---	---
Sample Status			ATTENTION	---	---

WEAR METALS

	method	limit/base	current	history1	history2
PQ	ASTM D8184	>200	14	---	---
Iron	ppm	ASTM D5185m	>250	2	---
Chromium	ppm	ASTM D5185m	>10	<1	---
Nickel	ppm	ASTM D5185m	>5	<1	---
Cadmium	ppm	ASTM D5185m		<1	---
Titanium	ppm	ASTM D5185m		0	---
Vanadium	ppm	ASTM D5185m		<1	---
Lead	ppm	ASTM D5185m	>25	0	---
Copper	ppm	ASTM D5185m	>75	3	---
Tin	ppm	ASTM D5185m	>5	0	---
Silver	ppm	ASTM D5185m	>5	<1	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		268	---
Magnesium	ppm	ASTM D5185m		<1	---
Manganese	ppm	ASTM D5185m		<1	---
Molybdenum	ppm	ASTM D5185m		<1	---
Phosphorus	ppm	ASTM D5185m		1053	---
Zinc	ppm	ASTM D5185m		1671	---

THICKENER/SOAP

	method	limit/base	current	history1	history2
Aluminum	ppm	ASTM D5185m		<1	---
Barium	ppm	ASTM D5185m		1	---
Calcium	ppm	ASTM D5185m		15	---
Sodium	ppm	ASTM D5185m		12	---
Lithium	ppm	ASTM D5185m		360	---
Sulfur	ppm	ASTM D5185m		8192	---

CONTAMINANTS


	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>150	4	---
Potassium	ppm	ASTM D5185m		4	---
Water	%	ASTM D6304	>0.1	0.028	---
ppm Water	ppm	ASTM D6304	>1000	283	---



GREASE CONDITION

	method	limit/base	current	history1	history2
Grease Color	*Visual		Yellow	---	---
Texture	*In-house		Buttery	---	---
NLGI Consistency	NLGI Scale *SKF Method		00-0	---	---







GREASE ANALYSIS



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0896570 **Received** : 11 Jan 2024
Lab Number : 06058568 **Diagnosed** : 22 Jan 2024
Unique Number : 10829950 **Diagnostician** : Aaron Black
Test Package : TEST (Additional Tests: A-FERR, CONSISTENCY, GREASECOLOR, ICP, KF, PQ, TEXTURE)

COALFIELD SERVICES
 3203 PEPPERS FERRY RD
 WYTHEVILLE, VA
 US 24382
 Contact: A MINTON
 aminton@coalfieldservices.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.




* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F:

FERROGRAPHY REPORT

Machine Id
MAYSVILLE HOIST
 Component
Grease
 Fluid
MOBIL Mobilux EP 0 (--- GAL)



FERROGRAPHY		method	limit/base	current	history1	history2
Ferrous Rubbing	Scale 0-10	*ASTM D7684		1		
Ferrous Sliding	Scale 0-10	*ASTM D7684		1		
Ferrous Cutting	Scale 0-10	*ASTM D7684				
Ferrous Rolling	Scale 0-10	*ASTM D7684				
Ferrous Break-in	Scale 0-10	*ASTM D7684				
Ferrous Spheres	Scale 0-10	*ASTM D7684				
Ferrous Black Oxides	Scale 0-10	*ASTM D7684				
Ferrous Red Oxides	Scale 0-10	*ASTM D7684				
Ferrous Corrosive	Scale 0-10	*ASTM D7684				
Ferrous Other	Scale 0-10	*ASTM D7684				
Nonferrous Rubbing	Scale 0-10	*ASTM D7684				
Nonferrous Sliding	Scale 0-10	*ASTM D7684				
Nonferrous Cutting	Scale 0-10	*ASTM D7684				
Nonferrous Rolling	Scale 0-10	*ASTM D7684				
Nonferrous Other	Scale 0-10	*ASTM D7684				
Carbonaceous Material	Scale 0-10	*ASTM D7684				
Lubricant Degradation	Scale 0-10	*ASTM D7684				
Sand/Dirt	Scale 0-10	*ASTM D7684				
Fibres	Scale 0-10	*ASTM D7684				
Spheres	Scale 0-10	*ASTM D7684				
Other	Scale 0-10	*ASTM D7684				

WEAR

This page left intentionally blank