

## **OIL ANALYSIS REPORT**

### JBS 258-46 **GARDNER DENVER S178609 - 4 - SUMITOMO** Component

Compressor

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.




SAMPLE INFORM	<b>MATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06059377	UCH05977736	UCH05804092
Sample Date		Client Info		27 Nov 2023	04 Sep 2023	05 Mar 2023
Machine Age	hrs	Client Info		73125	71816	67481
Oil Age	hrs	Client Info		8000	6500	2200
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	1	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m		2	<1	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	0	2
Lead	ppm	ASTM D5185m	>25	<1	0	0
Copper	ppm	ASTM D5185m	>50	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m	0.0	0	0	0
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m	0	<1	0	0
Magnesium	ppm	ASTM D5185m	0.0	<1	<1	<1
Calcium	ppm	ASTM D5185m	0.0	0	0	0
Phosphorus	ppm	ASTM D5185m	966	171	189	207
Zinc	ppm	ASTM D5185m	0	0	3	2
Sulfur	ppm	ASTM D5185m	1309	426	522	749
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	1	<1
Sodium	ppm	ASTM D5185m		0	0	2
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.172	0.52	0.43	0.22




# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2		
Visc @ 40°C	cSt	ASTM D445	39.9	45.3	44.9	44.7		
SAMPLE IMAGES		method	limit/base	current	history1	history2		
Color Color								
Bottom								



Contact/Location: STEVE SANDERS - UCJOHNAS