

OIL ANALYSIS REPORT

Sample Rating Trend





Area [0028] Machine Id CATERPILLAR 745D 13403 (S/N 3T606051) Component

Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Brake

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.

Fluid Condition

The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		WC0887973					
Sample Date		Client Info		08 Jan 2024					
Machine Age	hrs	Client Info		1176					
Oil Age	hrs	Client Info		1176					
Oil Changed		Client Info		Changed					
Sample Status				NORMAL					
CONTAMINATION	1	method	limit/base	current	history1	history2			
Water	AMINATION		>0.2	NEG					
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>350	12					
Chromium	ppm	ASTM D5185m	>5	<1					
Nickel	ppm	ASTM D5185m	>5	<1					
Titanium	ppm	ASTM D5185m	20	<1					
Silver		ASTM D5185m		0					
	ppm	ASTM D5185m	20	2					
Aluminum	ppm			_					
Lead	ppm	ASTM D5185m	>10	<1					
Copper	ppm	ASTM D5185m	>150	30					
Tin	ppm	ASTM D5185m	>5	<1					
Vanadium	ppm	ASTM D5185m		0					
Cadmium	ppm	ASTM D5185m		<1					
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		2					
Barium	ppm	ASTM D5185m		6					
Molybdenum	ppm	ASTM D5185m		<1					
Manganese	ppm	ASTM D5185m		<1					
Magnesium	ppm	ASTM D5185m		12					
Calcium	ppm	ASTM D5185m		3317					
Phosphorus	ppm	ASTM D5185m		1169					
Zinc	ppm	ASTM D5185m		1392					
Sulfur	ppm	ASTM D5185m		6308					
CONTAMINANTS		method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>400	190					
Sodium	ppm	ASTM D5185m		0					
Potassium	ppm	ASTM D5185m	>20	2					
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE					
Yellow Metal	scalar	*Visual	NONE	NONE					
Precipitate	scalar	*Visual	NONE	NONE					
Silt	scalar	*Visual	NONE	NONE					
Debris	scalar	*Visual	NONE	NONE					
Sand/Dirt	scalar	*Visual	NONE	NONE					
Appearance	scalar	*Visual	NORML	NORML					
Odor	scalar	*Visual	NORML	NORML					
Emulsified Water	scalar	*Visual	>0.2	NEG					
Free Water	scalar	*Visual		NEG					
				Contact/Location: MIKE WYATT - TRANEW					



Ē

OIL ANALYSIS REPORT



2	FLUID PROPERT	IES	method	limit/base	current	history1	history2		
	Visc @ 40°C	cSt	ASTM D445		40.0				
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2		
	Color				no image	no image	no image		
Jan8/24	Bottom				no image	no image	no image		
	GRAPHS	· · · ·		1					
۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱ ۱	Viscosity @ 40°C	S		Jan 8/24					
(201) 7 80 6 5	70 50 50 40								
	Jan 8/24 -			Jan8/24 .					
Certificate 12367 To discuss this sample report, co * - Denotes test methods that are	Laboratory: WearCheck USA - 501 Madison Ave., Cary, NC 27513Sample No.: WC0887973Recieved: 12 Jan 2024Lab Number: 06059678Diagnosed: 16 Jan 2024Unique Number: 10831060Diagnostician: Sean Felton						TRADER CONSTRUCTION CO. PO DRAWER 1578 NEW BERN, NC US 28563 Contact: MIKE WYATT mwyatt@traderconstruction.com T: (252)633-1399 106:2012) F: (252)638-4871		

Contact/Location: MIKE WYATT - TRANEW