

OIL ANALYSIS REPORT

Sample Rating Trend


NORMAL



CATERPILLAR 745D 13400 (S/N 3T606050)

Brake

{not provided} (--- GAL



Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the fluid.


Fluid Condition

The condition of the fluid is acceptable for the time in service.


.)						
SAMPLE INFORM	AATION.	method	oazoza limit/base	Jan2024	historyd	history/2
	MATION		imivbase	current	history1	history2
Sample Number		Client Info		WC0887963	WC0862938	
Sample Date		Client Info		05 Jan 2024	23 Oct 2023	
Machine Age	hrs	Client Info		1995	1054	
Oil Age	hrs	Client Info		941	1054	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>350	11	6	
Chromium	ppm	ASTM D5185m	>5	<1	0	
lickel	ppm	ASTM D5185m	>5	<1	<1	
itanium	ppm	ASTM D5185m		<1	<1	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>8	2	<1	
.ead	ppm	ASTM D5185m	>10	<1	0	
Copper	ppm	ASTM D5185m	>150	26	38	
in	ppm	ASTM D5185m	>5	<1	0	
/anadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		<1	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		67	0	
Barium	ppm	ASTM D5185m		4	2	
Molybdenum	ppm	ASTM D5185m		3	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m		37	15	
Calcium	ppm	ASTM D5185m		2997	2849	
Phosphorus	ppm	ASTM D5185m		1044	1076	
inc	ppm	ASTM D5185m		1305	1245	
Sulfur	ppm	ASTM D5185m		3836	4364	
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	99	151	
Sodium	ppm	ASTM D5185m		0	1	
Potassium	ppm	ASTM D5185m	>20	2	0	
VISUAL		method	limit/base	current	history1	history2
Vhite Metal	scalar	*Visual	NONE	NONE	NONE	
ellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
ree Water	scalar	*Visual		NEG	NEG	




OIL ANALYSIS REPORT




FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		41.6	39.4	
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image





Viscosity @ 40°C







Certificate L2367

Laboratory Sample No. Lab Number

: 06059682 Unique Number : 10831064 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0887963 Recieved Diagnosed

: 12 Jan 2024 : 16 Jan 2024 Diagnostician : Sean Felton

TRADER CONSTRUCTION CO. PO DRAWER 1578

NEW BERN, NC US 28563

Contact: MIKE WYATT mwyatt@traderconstruction.com

T: (252)633-1399 F: (252)638-4871

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)