

OIL ANALYSIS REPORT

Sample Rating Trend



WEAR



Machine Id
JOHN DEERE 843L-II 1DW843LBPNF714405

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

DIAGNOSIS

▲ Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

▲ Wear

The copper level is abnormal. Valve wear is indicated. Elemental level of copper (Cu) probably due to leaching of copper from copper components (i.e. cooling core) by the oil additives.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

▲ Fluid Condition

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		JR0179594	---	---
Sample Date	Client Info		12 Jan 2024	---	---
Machine Age	hrs	Client Info	446	---	---
Oil Age	hrs	Client Info	0	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			ABNORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Water	WC Method	>0.21	NEG	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >51	46	---	---
Chromium	ppm	ASTM D5185m >11	<1	---	---
Nickel	ppm	ASTM D5185m >5	▲ 19	---	---
Titanium	ppm	ASTM D5185m	<1	---	---
Silver	ppm	ASTM D5185m >3	0	---	---
Aluminum	ppm	ASTM D5185m >31	4	---	---
Lead	ppm	ASTM D5185m >26	<1	---	---
Copper	ppm	ASTM D5185m >26	▲ 333	---	---
Tin	ppm	ASTM D5185m >4	1	---	---
Vanadium	ppm	ASTM D5185m	0	---	---
Cadmium	ppm	ASTM D5185m	0	---	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	99	---	---
Barium	ppm	ASTM D5185m	0	---	---
Molybdenum	ppm	ASTM D5185m	184	---	---
Manganese	ppm	ASTM D5185m	4	---	---
Magnesium	ppm	ASTM D5185m	872	---	---
Calcium	ppm	ASTM D5185m	1234	---	---
Phosphorus	ppm	ASTM D5185m	970	---	---
Zinc	ppm	ASTM D5185m	1127	---	---
Sulfur	ppm	ASTM D5185m	2801	---	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >22	10	---	---
Sodium	ppm	ASTM D5185m >31	4	---	---
Potassium	ppm	ASTM D5185m >20	6	---	---
Fuel	%	ASTM D3524 >2.1	0.4	---	---


INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	0.6	---	---
Nitration	Abs/cm	*ASTM D7624 >20	8.3	---	---
Sulfation	Abs/.1mm	*ASTM D7415 >30	21.3	---	---


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	15.5	---	---
Base Number (BN)	mg KOH/g	ASTM D2896 13.6	8.1	---	---

OIL ANALYSIS REPORT










VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---
Precipitate	scalar	*Visual	NONE	NONE	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.21	NEG	---	---
Free Water	scalar	*Visual		NEG	---	---



FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	▲ 11.3	---	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0179594 **Received** : 16 Jan 2024
Lab Number : 06060856 **Diagnosed** : 18 Jan 2024
Unique Number : 10832238 **Diagnostician** : Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, PercentFuel, TBN)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)