

# **OIL ANALYSIS REPORT**

Sample Rating Trend







Machine Id STACKER Component

Hoisting Gearbox Fluid {not provided} (--- GAL)

#### DIAGNOSIS

# Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

# Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0819590		
Sample Date		Client Info		15 Jan 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	22		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>100	<1		
Copper	ppm	ASTM D5185m	>50	4		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		8		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		16		
Phosphorus	ppm	ASTM D5185m		342		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		10120		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	4		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.57		



# **OIL ANALYSIS REPORT**

VISUAL



	VISUAL		methoa	limit/base		nistory i	nistory∠
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Jan 15/24	Appearance	scalar	*Visual	NORML	NORML		
Jan	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
				1111/0430		,	mstoryz
	Visc @ 40°C	cSt	ASTM D445		216		
	SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
Jan15/24	Color				DIAZN	no image	no image
	Bottom					no image	no image
	Non-ferrous Meta Non-ferrous Meta Non-ferrous Meta			Jan15/24	Acid Number		
1.3-UT2) 2-6-7	200 200 150 4bnomal 50 50 50 50 50 50 50 50 50 50			0.66 (0,040 0.34 0.02 9 0.00 9 0.00 9 0.00	]		C L
	: WC0819590 : 06061325 : 10832707 : IND 2 contact Customer Ser	: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0819590 <b>Recieved</b> : 16 Jan 2024 : 06061325 <b>Diagnosed</b> : 17 Jan 2024 : 10832707 <b>Diagnostician</b> : Don Baldridge : IND 2 intact Customer Service at 1-800-237-1369.					
Denotes test methods that a tements of conformity to spec					JCGM 106:2012		4)838-868112 (814)833-725

Ē

Contact/Location: TERRY UPLINGER - THEERI