


OIL ANALYSIS REPORT

SCHTRUCK 6394 [SCHTRUCK]

Front Diesel Engine

PETRO CANADA DURON SHP 15W40 (10 GAL)





DIAGNOSIS

Recommendation Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

GAL)			Aug2023	Jan 2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0006501	SBP0005094	
Sample Date		Client Info		05 Jan 2024	30 Aug 2023	
Machine Age	hrs	Client Info		76498	38357	
Oil Age	hrs	Client Info		38141	38357	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	ABNORMAL	
CONTAMINATIO	N	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	0.2	
Water		WC Method	>0.2	NEG	NEG	
Glycol		WC Method		NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>65	52	<u> </u>	
Chromium	ppm	ASTM D5185m	>5	3	<u></u> 5	
Nickel	ppm	ASTM D5185m	>3	<1	1	
Titanium	ppm	ASTM D5185m	>5	0	<1	
Silver	ppm	ASTM D5185m	>2	0	<1	
Aluminum	ppm	ASTM D5185m	>35	15	49	
Lead	ppm	ASTM D5185m	>10	<1	0	
Copper	ppm	ASTM D5185m	>180	75	<u>▲</u> 186	
Tin	ppm	ASTM D5185m	>8	1	5	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	3	31	
Barium	ppm	ASTM D5185m		0	<1	
Molybdenum	ppm	ASTM D5185m	60	58	44	
Manganese	ppm	ASTM D5185m	0	2	6	
Magnesium	ppm	ASTM D5185m	1010	904	582	
Calcium	ppm	ASTM D5185m	1070	1207	1921	
Phosphorus	ppm	ASTM D5185m	1150	906	748	
Zinc	ppm	ASTM D5185m	1270	1174	942	
Sulfur	ppm	ASTM D5185m	2060	1958	2211	
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	5	9	
Sodium	ppm	ASTM D5185m		2	8	
Potassium	ppm	ASTM D5185m		42	141	
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.7	0.6	
Nitration	Abs/cm	*ASTM D7624		10.2	11.7	
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1	23.2	
FLUID DEGRADA	NOITA	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.3	26.6	
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.2	6.5	




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPERT	TES	method	limit/hase	current	history1	hietory2


FLUID FROFER	IIES	memou			HISTORY	HISTOLYZ
Visc @ 100°C	cSt	ASTM D445	15.4	13.2	1 0.0	



Non-ferrous Metals











Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10833193 Test Package : FLEET

: SBP0006501 : 06061811

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jan 2024 Diagnosed : 18 Jan 2024 Diagnostician : Wes Davis

SCHMIDT TRANSPORTATION - 605449

108 E Bay Road Plattsmouth, NE US 68048 Contact: NICK DOTY

doty@liquidtrucking.com T: (402)949-9398

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)